



DuPont™ Tyvek® 1070D Product Properties—English Units

Product Features:
Antistatic Treatment
Corona Treated

Specification Properties (English Units)

Property	Comparable Test Method	Units	Tyvek® 1070D
Basis Weight	ASTM D3776	oz/yd ²	2.00 [1.92–2.11]
Delamination	ASTM 2724 ¹	lb _f /inch	0.3 [0.1–0.5]

Notes: Specification properties are based on roll averages from samples taken uniformly across the sheet. Specification properties are controlled to a nominal value and released within specification; the ranges listed represent the controlled minimum and maximum values in which the product is released. The customer is responsible for determining that Tyvek® is suitable for the intended application.

1. Modified for speed and sample width.

Miscellaneous Properties (English Units)

Property	Comparable Test Method	Units	Tyvek® 1070D
Thickness	ASTM D1777 ¹ EN ISO 534 ¹	mils	7.5
Opacity	TAPPI T425 ² ISO 2471 ²	%	97
Elmendorf Tear, MD	ASTM D1424	lb _f	1.3
Elmendorf Tear, CD	ASTM D1424	lb _f	1.3
Tensile Strength, MD	ASTM D5035 ³ EN ISO 1924 ³	lb _f /inch	37
Tensile Strength, CD	ASTM D5035 ³ EN ISO 1924 ³	lb _f /inch	40
Thickness of shielding alloy		mils	1.0
TOTAL THICKNESS of ArmorSHIELD		mils	8.5



OutdoorPaper™

sales@outdoorpaper.com