


ABSTRACT

Test Material:	Sorber Acoustic Absorption Panels		
Test Standard:	ASTM E84-01 Standard Test Method for SURFACE BURNING CHARACTERISTICS OF BUILDING MATERIALS (ANSI 2.5, NFPA 255, UBC 8-1, UL 723)		
Test Date:	April 2, 2003		
Test Sponsor:	Clearsonic Mfg., Inc.		
Test Results:	FLAME SPREAD INDEX	=	0
	SMOKE DEVELOPED INDEX	=	65

The description of the test procedure and specimen evaluated, as well as the observations and results obtained, contained herein are true and accurate within the limits of sound engineering practice. These results are valid only for the specimen(s) tested and may not represent the performance of other specimens from the same or other production lots.


Omega Point Laboratories, Inc. authorizes the client named herein to reproduce this report only if reproduced in its entirety.

The test specimen identification is as provided by the client and Omega Point Laboratories accepts no responsibility for any inaccuracies therein.



Date: April 4, 2003

Guy A. Haby
Manager, Tunnel & Furniture Testing Services



Date: April 4, 2003

William E. Fitch, P.E. No. 55296
Executive Vice President



Omega Point Laboratories, Inc.
16015 Shady Falls Road
Elmendorf, TX 78112
(210) 635-8100 www.opl.com

