



EXCEL

Technical Data Sheet

READY ROAD REPAIR PERMANENT POTHOLE COLD PATCH #6430



Product Description

Ready Road Repair is a high quality, pre-mixed, asphalt "cold patch" compound. Combining carefully selected aggregate with a modified bitumen formula, Ready Road repair Pothole Patch is the best choice for all types of pavement repairs. It restores dangerous potholes and wide cracks within minutes, regardless of the weather. Suitable for use on both concrete and asphalt pavement, Ready Road Repair is highly recommended for spot repairs to driveways, parking lots, sidewalks, roads, loading ramps etc. Ready Road Repair can be applied year round to either wet or dry pavement. The most important benefit to remember is the fact that Ready Road Repair is the "PERMANENT PATCH" and remains in the repaired area indefinitely. Ready Road Repair is easy to apply with most repairs taking only a few minutes to complete.

Features and Benefits

- Ready to use.
- Sets Immediately
- Remains flexible and cohesive to -26°C (-15°F)
- Retains it's adhesive qualities even in wet applications.
- Ready Road Repair Pothole Patch is available in 22.7 kg (50 lbs) & 10 kg (22 lbs) Plastic Bags.

Application

PREPARATION:

Simply sweep out the area to be repaired with a bristled brush or broom. It is a good idea to remove any loose debris, dirt, ice or standing water from the area to be repaired. This will promote better adhesion and bonding.

APPLICATION:

1.ASPHALT:

No heating or mixing is required. Shovel Ready Road Repair into the pothole or crack, straight from the container. When the fault is especially deep, ie. over six inches, apply Ready Road Repair in two inch layers, compacting each layer in succession. Shovel enough material into the fault to slightly crown the "patch". When completed compress the "patch" with shovel or tamper. Area can be opened to traffic immediately

2.CONCRETE:

Apply as you would in Asphalt Application. When completed and ready to compress the

patch, sprinkle a coating of Portland Cement over the surface. The cement is to even the color between the patch and the concrete.
Put enough to cover the entire surface. Compress the "patch" with shovel or tamper.
Sweep off excess Portland Cement. Open to traffic.
Clean up with Mineral Spirits/Paint Thinner

Coverage

Depth and width of a pothole, crack, utility cut etc. will greatly influence the coverage rate achieved. A fifty-pound bag / 22.7 kg of Ready Road Repair will fill 5.6 sq.ft / 1.7 m² at 1" / 2.54 cm thick. A twenty two pound bag / 10 kg of ready Road Repair will fill 1.7 sq.ft / 0.22 m² at 1" / 2.54 cm thick.

Cautions

Always keep container tightly closed when not in use to prevent "hardening" over long periods of storage.

Physical Properties

Aggregate consists of 100% crushed and graded Limestone.

Limited Warranty

If this product is proven to have a manufacturing defect, we will provide you with replacement value or product, at our option, for the defective product. This commitment is our full representation regarding the product and is in lieu of all expressed or implied warranties and may not be extended by representatives, written sales information, drawings or otherwise. IN NO EVENT SHALL THE MANUFACTURER OR ITS AFFILIATES BE LIABLE FOR ANY INDIRECT, ASSOCIATED, INCIDENTAL OR CONSEQUENTIAL DAMAGES.