



# ASPELAND

## PRODUCT DESCRIPTION

<b>Article Number</b>	151NDSEK01KW240
<b>Surface Treatment</b>	Oil
<b>Refining Treatment</b>	Beveled 4-sided, brushed, handscraped, saw marks
<b>Dimensions</b>	95 1/4" x 7 3/8" x 5/8"
<b>Weight per Package</b>	49 lbs
<b>Area per Package</b>	29.27 sq ft
<b>Area Per Board</b>	4.878 sq ft

## DETAIL DESCRIPTION

All naturally occurring wood colour variations allowed, from light to dark brown. Sapwood may occur. The product includes very large sound and black knots and cracks. Knots and cracks will be present in all sizes and numbers.

## COLOUR CHANGE

Stained product - noticable color change over time.

## CERTIFICATE

## FACTS

<b>Wood Species</b>	White Oak
<b>Design</b>	1-strip
<b>Grading</b>	Expressive
<b>Range</b>	Kährs Supreme
<b>Collection</b>	Småland Collection
<b>Resandable</b>	2 times
<b>Natural/Stained</b>	Stained
<b>Brinell Value</b>	3, 7
<b>Joint</b>	Woodloc® 5S
<b>Floor heating</b>	Yes
<b>Wear-layer material</b>	Hardwood
<b>Wear-layer thickness</b>	1/8"
<b>Core material</b>	Pine/Spruce lamella
<b>Backside material</b>	Veneer
<b>Thickness</b>	5/8"
<b>Installation method</b>	Floating, glue-down
<b>EAN Code</b>	7393969039024

## TECHNICAL PROPERTIES

<b>Moisture content</b>	EN13183	7%±2%
<b>Minimun Mean Density kg/m³</b>		>500 kg/m³
<b>Reaction To Fire</b>	EN13501-1	Dfl-s1
<b>Formaldehyde Emission</b>	EN717-1	E1
<b>Content PCP</b>	CEN/TR14823	≤ 5 x 10-6n
<b>Breaking Strength N/mm²</b>	EN1533	NPD
<b>Thermal Conductivity</b>	EN12664	0,14 W/mK
<b>Thermal Resistance R-Value</b>		.11 (m2K/W)
<b>Biological Durability</b>	EN350-2	Class 1
<b>CARB2</b>		Compliant

