

ADVANCE® WATERBORNE INTERIOR/EXTERIOR ALKYD HIGH GLOSS F794

Features

- · Excellent durability
- Excellent flow and levelling properties
- · Extended open time
- · Very High Gloss
- Spatter resistant
- Easy application
- · Easy clean up
- Block resistant
- Interior/exterior use

General Description

A premium quality, waterborne alkyd enamel that delivers the desired flow and levelling characteristics of conventional alkyd paint. It provides a tough, high gloss finish that stands up to repeated washing. It is easy to apply, resists spattering, and cleans up with soap and water.

Recommended For

Ideal for interior doors, trim, cabinets, walls, and ceilings. For primed or previously painted wallboard, plaster, masonry, wood and metal. Recommended for exterior use on properly primed metal, masonry, and stable trim substrates such as cedar and redwood.

Limitations

- Depending on weather and drying conditions, it could take up to 30 days to reach optimum hardness.
- Do not use over exterior pine.
- Sand glossy alkyds before applying ADVANCE.

Product I	nformation	
Colours — Standard:	Technical Data◊ Pastel Base	
White (01), Black (80)	Vehicle Type Waterborne alkyd	
	Pigment Type Titanium Dioxide	
— Tint Bases:	Volume Solids 42%	
Benjamin Moore® Gennex® bases 1X, 2X, 3X, 4X	Coverage per 3.79 L at Recommended 400 – 500 sq. ft. Film Thickness 37.2 – 46.5 sq. m.	
— Special Colours: Contact your Benjamin Moore representative.	Recommended Film — Wet 3.6 mils Thickness — Dry 1.5 mils	
Certification:	Depending on surface texture and porosity. Be sure to estimate the right amount of paint for the job. This will ensure colour uniformity and minimize the disposal of excess paint.	
VOC compliant in all regulated areas.	Dry Time @ 25 °C − To Touch 4-6 Hours (77 °F) @ 50% RH − To Recoat 16 Hours	
Master Painters Institute MPI #157, 157 X-Green Class A (0-25) over non-combustible surfaces when tested in accordance with ASTM E-84	ADVANCE's full hardness and adhesion develop over time. Do not expose to heavy abrasion or return shelves/tabletops to service for at least 3-5 days to prevent damage to the finish. High humidity or cooler temperatures will prolong dry, recoat and cure times.	
	Dries By Evaporation, Oxidation	
	Viscosity 91 ± 3 KU	
Qualifies for LEED® v4 Credit (INTERIOR NON-FLAT) CHPS Certified (Collaboration for High Performance Schools)	Flash Point None	
	Gloss / Sheen High Gloss (85 min @ 60°)	
	Surface Temperature at Min. 10 °C (50 °F)	
(INIZION NON Y ZAI)	Application – Max 32.2 °C (90 °F)	
Customer Information Centre: 1-800-361-5898, info@benjaminmoore.ca, www.benjaminmoore.ca	Thin With Clean Water	
	Clean Up Thinner Clean Water	
	Weight Per 3.79 L 10.4 lbs	
	Storage Temperature - Min 4.4 °C (40 °F)	
	- Max 32.2 °C (90 °F)	
	Volatile Organic Compounds (VOC)	
	44 g/L	

♦Reported values are for Pastel Base. Contact Benjamin Moore for values of other bases or colours

Surface Preparation

Surfaces to be painted must be clean, dry, and free of dirt, dust, grease, oil, soap, wax, scaling paint, water-soluble materials, and mildew. Remove any peeling or scaling paint and sand these areas to feather edges smooth with adjacent surfaces. Glossy areas should be dulled. Drywall surfaces must be free of sanding

New plaster or masonry surfaces must be allowed to cure before applying base coat. Cured plaster should be hard, have a slight sheen and maximum PH of 10; soft, porous or powdery plaster indicates improper cure. Never sand a plaster surface; knife off any protrusions and prime plaster before and after applying patching compound. Poured or pre-cast concrete with a very smooth surface should be etched or abraded to promote adhesion, after removing all form release agents and curing compounds. Remove any powder or loose particles before priming. Wood substrates must be thoroughly dry.

Difficult Substrates: Benjamin Moore offers a number of specialty primers for use over difficult substrates such as bleeding woods, grease stains, crayon markings, hard glossy surfaces, galvanized metal, or other substrates where paint adhesion or stain suppression is a particular problem. Your Benjamin Moore retailer can recommend the right problem solving primer for your special needs.

WARNING! If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by logging onto Canada http://www.hc-sc.gc.ca/ewh-semt/contaminant sked questions-questions posees-eng.php

Primer/Finish Systems

New surfaces should be fully primed, and previously painted surfaces may be primed or spot primed as necessary. For best hiding results use Benjamin ADVANCE® Waterborne Interior Alkyd Primer tinted to the approximate finish coat colour. Special Note: Certain custom colours require a Deep Colour Base Primer tinted to a special prescription formula to achieve the desired colour. Consult your retailer.

Wood and engineered wood products:

Primer: ADVANCE® Waterborne Interior Alkyd Primer (K790), Fresh Start® Multi-Purpose Latex Primer (F023) or Fresh Start® Multi-Purpose Oil Based Primer (F024)

Finish: 1 or 2 coats ADVANCE® Waterborne Alkyd High Gloss (F794)

Cabinetry: All surfaces to be roughened by sanding (220 grit or coarser) before priming; light sanding between coats allows for a smoother finish; all dust must be cleaned.

Wood, MDF & Thermofoil:

Primer: 1 coat ADVANCE® Waterborne Interior Alkyd Primer (K790) Finish: 1 or more coats of ADVANCE® Waterborne Alkyd High Gloss (F794)

Laminate (Formica):

Primer: Fresh Start® High-Hiding All Purpose Primer (K046)

Finish: 1 or more coats of ADVANCE® Waterborne Alkyd High Gloss

(F794)

Plastic (Vinyl) veneer:

Primer: 1 coat of ADVANCE® Waterborne Interior Alkyd Primer (K790) after removing plastic veneer by sanding away (an electric sander with a 100 grit

paper works fine; manual sanding may need to be vigorous)

Finish: 1 or more coats of ADVANCE® Waterborne Alkyd High Gloss (F794)

Primer: ADVANCE® Waterborne Interior Alkyd Primer (K790) or Fresh Start®

Multi-Purpose Latex Primer (F023)

Finish: 1 or 2 coats ADVANCE® Waterborne Alkyd High Gloss (F794)

Primer: Fresh Start® Multi-Purpose Latex Primer (F023) or Fresh Start® High-

Hiding All Purpose Primer (K046)

Finish: 1 or 2 coats ADVANCE® Waterborne Alkyd High Gloss (F794)

Rough or Pitted Masonry:

Primer: Ultra Spec® Masonry Interior/Exterior Hi-Build Block Filler (K571) Finish: 1 or 2 coats ADVANCE® Waterborne Alkyd High Gloss (F794)

Smooth Poured or Pre-cast Concrete:

Primer: Ultra Spec® Masonry Interior / Exterior 100% Acrylic Masonry Sealer

(K608) or Fresh Start® Multi-Purpose Latex Primer (F023)

Finish: 1 or 2 coats ADVANCE® Waterborne Alkyd High Gloss (F794)

Ferrous Metal (Steel and Iron):

Primer: Ultra Spec HP® Acrylic Metal Primer (FP04) or Super Spec HP® Alkyd

Metal Primer (KP06)

Finish: 1 or 2 coats ADVANCE® Waterborne Alkyd High Gloss (F794)

Non-Ferrous Metal (Galvanized & Aluminum)

All new metal surfaces must be thoroughly cleaned with Corotech® Oil & Grease Emulsifier (V600) to remove contaminants. New shiny non-ferrous metal surfaces that will be subject to abrasion should be dulled with very fine sandpaper or a synthetic steel wool pad to promote adhesion

Primer: Ultra Spec HP® Acrylic Metal Primer (FP04)

Finish: 1 or 2 coats ADVANCE® Waterborne Alkyd High Gloss (F794)

Hard glossy alkyd surfaces: Abrasion by sanding leads to optimum adhesion.

Repaint, All Substrates: Prime bare areas with the primer recommended for the substrate above. Sand glossy alkyds before applying ADVANCE.

Application

Stir thoroughly before and during use. Apply one or two coats.

Paint Application: For best results, use a premium Benjamin Moore® customblended nylon/polyester brush, premium Benjamin Moore® Microfibre roller, or a similar product. Apply paint generously from unpainted area into wet area. This product can also be sprayed.

Extra ventilation is necessary under humid conditions to speed the dry time of ADVANCE, especially when the paint is applied over sealed, hard, non-porous surfaces. The chart below is for general guidance.

9		
Mild conditions	Severe conditions	Very severe conditions
Dry (RH < 50%), and temperature between 21 °C (70 °F) and 32 °C (90 °F)	(RH > 50%), and/or temperature between 10 °C (50 °F) and 21 °C (70 °F)	RH > 85%, or temperature <10 °C (50 °F)
ADVANCE will dry normally. Dry to touch: 4-6 hours To Recoat: 16 hours	ADVANCE will dry slower than normal unless the following is done to speed the dry time: Ventilate the room with a fan and/or turn on A/C to lower the humidity.	Do not apply ADVANCE

Spray, Airless:

Fluid Pressure — 1,500 - 2,500 PSI;

Tip - .011 - .015 Orifice

Thinning/Clean up

Thinning is unnecessary, but if required to obtain desired application properties, a small amount of clean water may be added. Never add other paints or solvents. Clean up with warm soapy water. Brushes and rollers should be given a final rinse with mineral spirits to remove residual alkyd. Spray equipment should be given a final rinse with mineral spirits to prevent rusting.

Environmental Health & Safety Information

Use only in a well ventilated area. Keep container closed when not in use. In case of spillage, absorb with inert material and dispose of in accordance with local regulations. Wash thoroughly after handling.

KEEP OUT OF REACH OF CHILDREN PROTECT FROM FREEZING

Refer to Safety Data Sheet for additional health and safety information

Benjamin Moore & Co., Ltd. 8775 Keele St., Concord, ON L4K 2N1 1-800-361-5898 www.benjaminmoore.ca M72 F794 CE 031317 ADVANCE, Benjamin Moore, Fresh Start, Gennex, Green Promise, Super Spec HP, Ultra Spec, Ultra Spec HP and the triangle "M" symbol are registered trademarks of Benjamin Moore & Co., Ltd. All other marks are the property of their respective owner. This product is not endorsed by or a division of CHPS. This product is provided by Benjamin Moore, not CHPS. ©2011, 2017 Benjamin Moore & Co., Ltd. All rights Reserved