



Clear Laminating System

Clear, UV Stable Epoxy Resin for high colorwork laminations, coatings, and marine epoxy applications.

Product Overview CLR is a clear, UV stabilized, general use, laminating resin for composites, coating, and adhesive applications. It has an ideal viscosity for a wide range of applications that use hand layup techniques with fast room temperature cures. CLR is a USDA Certified BioPreferred[®] Product with 29% biobased content.







		1731	JLOW
MECHANICAL DATA			
Tensile Modulus (ASTM D638)	450,000 psi (3.1 GPa)	440,000 psi (3.0 GPa)	468,000 psi (3.2 GPa
Tensile Strength (ASTM D638)	9,500 psi (65.5 MPa)	9,500 psi (65.5 MPa)	9,800 psi (67.6 MPa)
Elongation (ASTM D638)	6%	5%	6%
Flexural Modulus (ASTM D790)	440,000 psi (3.0 GPa)	440,000 psi (3.0 GPa)	430,000 psi (2.9 GPa)
Flexural Strength (ASTM D790)	14,000 psi (96.5 MPa)	13,500 psi (93.1 MPa)	14,580 psi (100.5 MPa)
Compression Strength (ASTM D695)	11,330 psi (78.1 MPa)	11,330 psi (78.1 MPa)	12,520 psi (86.3 MPa)
Tg Ultimate (DSC, midpoint)	148°F (64°C)	151°F (66 °C)	142°F (61°C)
Hardness (Shore D)	70-80	70-80	70-80

DAIA			
Mix Ratio (by volume)	2:1	2:1	2:1
Mix Ratio (by weight)	100:43	100:45	100:43
Viscosity (A/B/Mixed @ 77°F/25°C)	2300/180/990	2300/280/1040	2300/140/700
Component Density (specific density @ 77°F/25°C)	1.14 (resin), 0.98 (hardener)	1.14 (resin), 1.01 (hardener)	1.14 (resin), 0.98 (hardener)
Mixed Density (specific density @ 77°F/25°C)	1.08	1.09	1.08
Pot Life (@ 77°F/25°C)	18 min	21 min	43 min
Tack Free Time (@ 95°F/35°C)	2 hrs	4 hrs	8 hrs
Recommended Full Cure	7 days @ 77°F/25°C	7 days @ 77°F/25°C	7 days @ 77°F/25°C Post cure recommended

ENVIRONMENTAL DATA			
VOC Content (ASTM D2369)	0.16 lbs/gal (19.5 g/L)	0.26 lbs/gal (31.5 g/L)	0.00 lbs/gal (0.23 g/L)
Mixed Biobased Carbon Content (ASTM D6866)	20%	20%	21%

This technical information is provided in good faith and is based on the best knowledge of Gougeon Brothers, Inc. We cannot guarantee this data because conditions of product use are beyond our control. TDS revised May 2020. © Gougeon Brothers, Inc. 2020

AMERICAS ENTROPY RESINS info@entropyresins.com 310.882.2120 100 Patterson Ave., Bay City, MI 48706 entropyresins.com





