





Technical Data		
Description	Standard	Performance
Weight	EN-13859-2	195 g/m <sup>2</sup> ± 10%
Fire Behaviour	EN-13501-1	В
Smoke development		S1
Flaming droplets		dO
Sd-Value	EN 13859-2	0.13 ± 0.03 m
Air tightness [50 Pa]		0,01 m³/m², h, Pa
Resistance to water penetration	EN 1928	W1 (Before & after ageing)
Nail Tear Resistance MD / CD*	EN-13859-2	210 / 300 N
Elongation MD / CD* before	EN-13859-2	50 / 70 % ± 15%
and after ageing		40 / 60 % ± 15%
Tensile Strength MD/CD* before	EN-13859-2	340 / 240 N / 5cm ± 30%
and after ageing		320 / 220 N / 5cm ± 30%
Temperature resistance		-40°C to +80°C
CE labelling		Available
UV Resistance		> 10 years**
Resistance to water pressure		> 400 [cmWS]
Roll length		1.5 / 50 m
Vapour Permanence	ASTM E96	14.92
Surface Burning	ASTM E96	CLASS A

## **Advantages**

- √ Increased Fire Resistance B-s1,d0
- √ Monolithic Technology
- $\sqrt{}$  High quality properties premium membrane
- √ High Level of UV Resistance
- √ Ideal Airtightness and Vapour transmission
- √ Long term resistance to driving rain
- √ Windproof / Diffusion open
- √ Systematic safety and energy-efficient solution
- √ BBA pending

## **Monolithic TPU Technology**

2-Ply sarking, roof underlay and wind barrier with **Next Generation Monolithic TPU functional layer.** Excellent aging resistance due to Monolithic Technology.

This Monolithic TPU layer results in a stronger, more flexible membrane with greater resistance to corrosion and abrasion compared to the micro-porous membranes that are prevalent on the market.

More importantly the Monolithic TPU layer creates a complete wind tight, waterproof membrane that actively expels out any water/ humidity unlike most micro-porous membranes that rely on small pores (which have the tendency to block).















\*MD = longitudinal CD = transversal \*\*does not apply in the case of open air weathering, but only when clad with a distance of approx. 5 cm and a maximum joint area of 40%

"The information provided is based on current knowledge and experience. This data sheet may become invalid and we reserve the right to make changes to designs and processes as we continually improve quality. Processing instructions including full system component details should be adhered to. Visit partel com for the most up to date information"











## **General Conditions**

Partel EXOPERM MONO DURO 200 membranes should be laid with the printed side facing the installer.

Membranes are suitable as roofing/decking underlays. They are resistant to driving rain and wind. Apply onto the existing support structure, parallel to eaves with overlaps of 100mm (4") in a taught manner. It should be nailed or screwed under the overlapped section.

Tape all joints using CONEXO MULTISEAL or VARA SEAL. Use Nail Seal underneath all battens.

Penetrations should be sealed using **KABSEAL** or **CONLEX BUTYL** and edge connections can be sealed with **ACRABOND**, **ACRALINE ROLL** or Partel tapes. Cross battens are recommended for ventilation and additional security. Wall membranes are suitable only for wall installation. Roof membranes can be used on walls and roof. Partel membranes can be used as temporary roof cover for 3 months, roof pitch must be 15' or greater.

During installation membranes should be immediately secured or fixed down to avoid wind damage.

Connection joints should be free from tensile strain. Acrylic base adhesive tapes are pressure activated, sufficient pressure is required to ensure a long lasting bond. A smoother physical substrate will result in optimum adhesion between tape and surface. It is the responsibility of the applicator to check the substrate for suitability, adhesion tests are recommended in non standard situations. Use **ACRAPRIME SPRAY** to prime all rough, porous or dusty surfaces.





