


SealDryFR™ Moisture Barrier Tape



- Backing:** FR Interior-Grade Aromatic Polyurethane
- Adhesive:** Hydrophobic Acrylic
- Liner:** Blue HDPE
- Colors:** Transparent
- Specifications:** FAR 25.853(a), BMS 8-346 Type I, Class 3; Bombardier BAMS 535-007 Type VI
- Size Options:** Incremental sizes 1/4" - 48" x 108Ft

Applications

- Aircraft corrosion protection
- Abrasion guard
- Aircraft seat track protection
- Cargo area moisture protection
- Floor seam protection for wet areas of aircraft

Features

- Polyurethane Film Backing
- Hydrophobic Acrylic
- Blue HDPE Liner

Benefits

- Lightweight to provide significant weight savings
- Flame retardant, self extinguishing
- No plasticizers or PBDEs (polybromiated diphenyls)
- Tough and abrasion resistant
- Excellent adhesion
- Clean removal, no residue
- Repositionable for ease of use
- Mold and fungus resistant
- Die cuttable

Typical Test Values

	Standard UOM		Metric UOM		Test Method
Total Thickness	6.0	mils	0.152	mm	PSTC-133
Adhesion to Steel (initial)	28	oz/in	3.06	N/cm	ASTM D-3330
Adhesion - 24hrs to Aluminum	35	oz/in	3.83	N/cm	ASTM D-3330
Adhesion - 24hrs to BMS 4-20 Panel	35	oz/in	3.83	N/cm	ASTM D-3330
Adhesion - 7d @ 160°F Alum	53	oz/in	5.80	N/cm	ASTM D-3759
Adhesion - 7d @ 160°F BMS 4-20	65	oz/in	7.11	N/cm	ASTM D-3759
Tensile Strength	34	lb/in	59.54	N/cm	ASTM D-3759
Elongation	550%				
Operating Temperature	-10 °F to 250 °F		-23 °C to 157 °C		
Abrasion/Wear Index	2.6				ASTM D-4060
Puncture Resistance	11	lbs	4.99	kg	ASTM D-1000
Weight	5.00	oz/yd ²	169.53	g/m ²	
Water Vapor Transmission	5.2 g/100 in ²				ASTM F-1249

Recommended Storage Conditions: 40-60% Humidity, 40 - 80 °F
Standard Shelf Life (at 25 °C): 24 months from date of manufacture

The information presented herein was prepared at BERRY PLASTICS CORPORATION (25 Forge Parkway Franklin, MA 02038) by qualified technical personnel. To Berry Plastics' knowledge it is true and accurate. However, the information and recommendations are furnished for these products with the understanding that the purchaser or user, as the case may be, will independently determine that the product is suitable for the intended use, and that such use complies with all applicable federal, state and local laws and regulations. The data are submitted only for the user's information and consideration, and do not constitute a warranty of any kind (including but not limited to a warranty of merchantability or of fitness for a particular purpose), or a representation for which BERRY PLASTICS assumes any legal responsibility.