

# **SCHÖNOX HS STURDY**

# Hybrid-Active-Dry-Technology based Rapid Drying Repair

# and Smoothing Compound

Suitable to provide a smooth finish on various substrates in interior areas. SCHÖNOX HS STURDY can be installed as a true featheredge.



# **Product characteristics**

- EMICODE EC 1: very low emission
- does not support mold growth
- for interior use only
- heavy duty
- featheredge achievable
- exceptional hardness and strength
- fast drying
- Iow dust
- suitable for underfloor heating systems
  layer thickness above featheredge up to
  2% (is seen used of index of
- 2" (in small, well defined areas without limitation)suitable for castor wheels loadings
- suitable for castor wheels load
- very smooth surface

#### Applications SCHÖNOX HS STURDY is suitable for smoothing and leveling of:

- concrete, cement substrates
- floor leveling compounds
- gypsum substrates
- gypsum substrates
  old substrates such as ceramic tiles
- old, water-resistant adhesive residues
- wooden substrates
- stair steps and wall breakouts

# Requirements of substrate

- Subfloors must be smooth, sound, clean, dry and free of any contaminants which may hinder adhesion.
- Surface treatments or any "friable" areas of the subfloor must be mechanically removed back to a sound base and the substrate repaired with SCHÖNOX repair compounds as required.
- All slabs on or below grade level must be known to have an intact vapor retarder directly beneath the concrete in conformance to the relevant standards. If in doubt, please contact our SCHÖNOX Technical Service for further advise.
- This product is not a vapor barrier and will allow free passage of moisture. Follow the directions of the floor covering manufacturer regarding the maximum allowable substrate moisture content and test the substrate prior to installing SCHÖNOX HS STURDY. Where substrate moisture exceeds the maximum allowed then application of SCHÖNOX SDG PLUS, SCHÖNOX MR 18 or SCHÖNOX EPA may be used to suppress residual moisture.
- Gypsum substrates should always be dry. Do not use moisture mitigation systems on gypsum substrates.
- Old water-soluble adhesives should be removed completely, old water-resistant adhesives should be mechanically removed as far as possible. The complete mechanical

removal of cutback (i.e. grinding, sanding, blasting) can be hazardous as old cutback adhesive may contain asbestos. Do not sand or grind adhesive residue. Refer to the Resilient Floor Covering Institute's publication "recommended work practice for removal of resilient floor coverings" for instruction. Prime remaining adhesive residues accordingly.

- The use of trowelable patching compounds to mask the presence of adhesive residues can be used successfully, but only when the new adhesive to be used does not react with the old residue, and the floor covering to be installed will not be affected by adhesive bleed-through.
- All cement based or wooden substrates must be solid, thoroughly clean and free of oil, wax, grease, asphalt, latex and gypsum compounds, curing compounds, sealers and any contaminant that might act as a bond breaker. If necessary, mechanically clean the floor down to sound, solid surface.
- Solidly bonded non-porous substrates such as ceramic tile and terrazzo must be thoroughly cleaned and abraded including the complete removal of existing waxes and sealers, dust, dirt, debris and any other contaminant that may act as a bond breaker.
- Substrates such as epoxi or urethane based sealers/coatings are primed with SCHÖNOX SHP following the referring product data sheet prior to apply SCHÖNOX HS STURDY.
- The requirements of the relevant valid standards (such as ASTM 2873-13), guidelines and data sheets apply.
- Vacuum substrates thoroughly.

# Priming

- gypsum substrates (sanded and vacuumed)
  - no priming required when used as a true featheredge up to 1/4".
  - prime with SCHÖNOX KH FIX when used as a repair mortar above 1/4".
- cement substrates such as: - concrete
- prime with SCHÖNOX VD (1:3) or KH FIX.
- non porous substrates such as:
  - ceramic tiles (thoroughly cleaned and abraded)
  - terrazzo
- water-resistant adhesive residues (removed as far as possible)
- prime with SCHÖNOX SHP. • wooden substrates such as
  - OSB board, plywood (well screwed and/ or bonded)

prime with SCHÖNOX SHP.

# **Technical data**

- pot life: approx 15 minutes
- ready for foot traffic: after approx. 30 minutes
- ready for covering:
  after approx. 30 minutes when applied as a true featheredge
   after approx. 4 hours at 2"
- arter approx. 4 nours at 2
- working temperature: 41°F 90°F
- coverage per unit of 15kg / 33lb.:
  approx. 600 sq.ft. when applied as a true featheredge
  - approx. 100 sq.ft. at 1/8"
- (depending on substrate conditions)compressive strength (ASTM C109):
- 30 N/mm² / 4,400 psi after 28 days ■ flexural strength (ASTM C348):
- approx. 7 N/mm² / 1300 psi after 28 days
- initial Set (ASTM C191): approx. 20 minutes
- final Set (ASTM C191): approx. 30 minutes
- flammability (ASTM E84):
  - Flame Spread 0; Smoke Development 0

All values are approximate, are subject to local climatic fluctuations based upon conditions at 70°F with atmosphere of less than 65 % relative humidity following the recommended mixing ratio. Do not install underlayment or topping before the substrate has dried thoroughly.





# **SCHÖNOX HS STURDY**

#### Mixing ratio

- mix each 15kg / 33lb. bag with 3.8 4.6 May help contribute to LEED v4 certification liters / 4 - 5 quarts of water
- We recommend to extend SCHÖNOX HS STURDY with dry, clean aggregate (aggregate is added last) at a layer ■ MRc1 - up to 2 points thickness above 1/2": type and amount of aggregate used will affect product ■ MRc2 - 1 point performance. As qualities of locally available aggregates vary, we recommend ■ MRc3 - 1 point to perform tests prior to use on a larger scale.
- Do not overwater!

# **Recommended method of** working

- Using a clean mixing bucket, add SCHÖNOX Declaration number: HS STURDY to cold, clean water to form a homogeneous mixture. Mix thoroughly for approx. 3 minutes using a heavy-duty drill Instructions (min. 600 rpm) to obtain a lump-free mix. Or mix smaller volumes by hand to consistency. Apply, smooth and shape the leveling compound using a stainless steel smoother or a smoothing trowel.
- Do not mix more material than can be applied within 15 minutes.
- Protect curing SCHÖNOX HS STURDY layers from high ambient temperatures, direct sunlight and draughts.
- Clean tools in water immediately after use.

# Packaging

■ 15kg / 33lb. net weight in paper bags

# Storage

- Store in cool and dry conditions.
- Shelf life: 12 months unopened.
- End of shelf life does not generally indicate the end of the products suitability for the intended use. Always test in a small area.

# Disposal

■ Empty packaging and dispose of in accordance with federal, state and local waste disposal regulations.

#### **VOC Content**

■ 0g/l (calculated), SCAQMD 1113

#### LEED

- of projects in the categories: ■ EQc2 - 3 points
- Low-Emitting Materials
- Life-Cycle Impact Reduction
- **Environmental Product Declaration**
- Sourcing of Raw Materials
- MRc4 1 point Material Ingredients

#### **Environmental Product** Declaration (EPD)

- FPD-FFI-20160017-IBG1-FN

- Do not use in areas of constant water exposure (such as interior swimming pools).
- Always install an adequate number of properly located test areas, to include the finish flooring, to determine the suitability of the product for its intended use. As floor coverings vary, always contact and rely upon the floor covering manufacturer for specific directions such as maximum allowable moisture content, adhesive selection, and intended end use of the product.
- Low substrate temperatures and/or high ambient humidity require longer drying times.

### Precautions

- SCHÖNOX HS STURDY contains gypsum. Avoid eye and skin contact. In case of contact, rinse immediately with plenty of water. In case of contact with eyes seek additional medical advice. Mix in a well ventilated area and avoid breathing powder or dust
- Never mix with cement or additives other than SCHÖNOX approved products. Observe the basic rules of concrete work. Do not install below 41°F surface temperature. Install quickly if substrate is warm.

KEEP CONTAINER TIGHTLY CLOSED • KEEP OUT OF REACH OF CHILDREN • NOT FOR INTERNAL CONSUMPTION • FOR

KEEP CONTAINER TIGHTLY CLOSED • KEEP OUT OF REACH OF CHILDREN • NOT FOR INTERNAL CONSUMPTION • FOR INDUSTRIAL USE ONLY • FOR PROFESSIONAL USE ONLY • SCHONOX products are supplied in the USA by SCHONOX HPS North America, a business unit of HPS North America, Inc. (HPS SCHONOX). • For further information and advice regarding transportation, handling, storage and disposal of chemical products, users should refer to the actual Safety Data Sheets containing physical, ecological, toxicological and other safety related data. Read the current actual Safety Data Sheets fore using the product. In case of emergency, call GBK/Infortac ID 108313 at 1 800 535 5053 (USA) or 001 352 323 3500 (International). HPS SCHONOX warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within shelf life. User determines suitability of product for intended use and assumes all risks. Buyer's sole remedy shall be limited to the purchase price or replacement of product exclusive of labor or cost of labor. NO OTHER WARRANTIE SEXPRESSED OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABULTY OR FITNESS FOR A PARTICULAR PURPOSE. HPS SCHONOX SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. HPS SCHONOX SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS. Sale of SCHÖNOX products are subject to the Terms and Conditions of Sale which are available at www.schonox.us. Terms and Conditions of Sale which are available at www.schonox.us.

Prior to each use of any SCHÖNOX product, the user must always read and follow the warnings and instructions on the product's most current product label, Product Data Sheet and Safety Data Sheet which are available at www. schonox.us, or by calling the HPS SCHÖNOX Technical Service Department at 855-391-2649. Nothing contained in any SCHÖNOX materials relieves the user of the obligation to read and follow the warnings and instruction for each SCHÖNOX product as set forth in the current product label, Product Data Sheet and Safety Data Sheet prior to product use. This product data sheet supersedes all previous editions.





Management system certified to ISO 9001 and 14001 by SQS.

#### In North America provided by:

HPS North America, Inc 511 Wilhite Street Florence, AL 35630 Phone: 256.246.0345 Fax∙ 256.246.0346 Email: info@hpsubfloors.com http://www.hpsubfloors.com

