

PHYSICAL PROPERTIES	
WEIGHT	0.27 lb/ft ² - 1.3 kg/m ²
COMPOSITION	100% Recycled Polyester
Longitudinal view	

MECHANICAL PROPERTIES	
Test method	Lab-TME 2T : adapted from NF G 071-119 or NEQ ISO 5081
Tensile strength	13442 lb/ft - 200 kN/m - 20 t/m
Elongation at break (%)	
Tensile strength	8065 lb/ft - 120 kN/m - 12 t/m
Elongation at break (%)	
Compression	1740 psi - 12 Mpa (N/mm ²)

CHEMICAL PROPERTIES	
Moisture regain 68°F 20°C - 65% HR	0.4%
Acid resistance	Good
Alkali resistance	Good
Solvent resistance	Good
Resistance to hydrocarbons : Kerosene F34, F35. Military lubricants F54. Domestic oil XF10	Good
Resistance to aviation hydraulic fluids (Ex. : Skydrol – HyJet IV A plus (Exxon))	Excellent (no physical deterioration after 18 days of wetting. 100% mechanical characteristics).
UV and weather resistance	Excellent
Micro-organisms resistance	Excellent
Urea and Liquid manure resistance	Excellent

THERMAL PROPERTIES	
Useable temperature	-40°F / +176°F -40°C / + 80°C
Softening temperature	428°F 220°C
Melting temperature	500°F 260°C
Degradation temperature	572°F 300°C
Combustion behaviour	Self-extinguishing upon removal of the flame

The technical data are not binding and not expressly warranted characteristics of the goods.



Recpath™



Helipad™



Mobi-Ramp™



Mobi-Fence™