

EXP12180 (12V 18Ah)

Specification

Cells Per Unit	6					
Voltage Per Unit	12					
Nominal Capacity	18Ah@20hour-rate to 1.75V per cell @77°F					
Weight	Approx. 11.46 lbs (Tolerance±3.0%)					
Internal Resistance	Approx. 16 m Ω					
Terminal	NB					
Max. Discharge Current	180A (5 sec)					
Short Circuit Current	750A					
Design Life	6~8 years (Float charging)					
Max. Charging Current	5.4 A					
Reference Capacity	C3 13.9AH C5 15.7AH C10 16.8AH C20 18.0AH					
Standby Use Voltage	13.7V~13.9V @ 77°F Temperature Compensation: -3mV/°C/Cell					
Cycle Use Voltage	14.6 V~14.8V @ 77°F Temperature Compensation: -4mV/°C/Cell					
Operating Temperature Range	Discharge: -4°F~140°F Charge: 32°F~122°F Storage: -4°F~140°F					
Normal Operating Temperature Range	77°F±41°F					
Self Discharge	EXP Valve Regulated Lead Acid (VRLA) batteries can be stored for up to 6 months at 77°F, after which recharging is recommended. The monthly self-discharge ratio is less than 3% at 77°F. Please ensure that you charge the batteries before using them.					

3.03

A.B.S. UL94-HB, UL94-V0 Optional.




The EXP series is a general-purpose battery with a designed life of 6~8 years in float service. It meets the standards of IEC, JIS, BS, GB/T, and YD/T. With advanced AGM valve-regulated technology and high-purity raw materials, the EXP series battery maintains high consistency for better performance and reliable standby service life. It is suitable for UPS/EPS, medical equipment, emergency lighting, and security system applications.




MH 61046 G4M20206-0910-E-16

Container Material

Dimensions







Unit: inch

7.13 ± 0.06in

3.03 ± 0.06in

6.57 ± 0.06in

6.57 ± 0.06in

NB

Constant Current Discharge Characteristics : A (77°F)												
F.V/Time	5MIN	10MIN	15MIN	30MIN	1HR	2HR	3HR	4HR	5HR	8HR	10HR	20HR
1.60V	75.88	53.63	38.77	22.27	12.22	7.503	5.640	4.553	3.773	2.428	1.972	1.041
1.65V	70.56	50.68	37.06	21.38	11.80	7.263	5.466	4.430	3.675	2.401	1.948	1.025
1.70V	63.67	46.65	34.71	20.43	11.42	7.024	5.317	4.310	3.579	2.364	1.919	1.012
1.75V	57.04	42.70	32.30	19.53	11.00	6.778	5.159	4.199	3.489	2.331	1.893	1.000
1.80V	50.09	38.66	29.83	18.67	10.58	6.536	4.999	4.079	3.399	2.291	1.869	0.990
1.85V	39.75	31.59	24.75	16.08	9.488	5.988	4.621	3.791	3.170	2.151	1.760	0.940


Constant Power Discharge Characteristics : WPC (77°F)												
F.V/Time	5MIN	10MIN	15MIN	30MIN	1HR	2HR	3HR	4HR	5HR	8HR	10HR	20HR
1.60V	125.8	91.16	67.77	40.44	22.96	14.22	10.77	8.742	7.272	4.742	3.877	2.050
1.65V	118.3	87.80	65.75	39.23	22.30	13.83	10.48	8.537	7.110	4.699	3.835	2.021
1.70V	109.2	82.32	62.51	37.88	21.71	13.45	10.24	8.336	6.949	4.637	3.782	1.999
1.75V	100.0	76.71	59.01	36.58	21.04	13.04	9.981	8.154	6.798	4.582	3.737	1.977
1.80V	89.68	70.65	55.26	35.31	20.36	12.64	9.710	7.948	6.646	4.514	3.694	1.960
1.85V	72.68	58.76	46.51	30.72	18.37	11.64	9.016	7.415	6.218	4.247	3.482	1.863


(Note) The above characteristics data are average values obtained within three charge/discharge cycle not the minimum values.


The battery must be fully charged before the capacity test. The C20 should reach 95% after the first cycle and 100% after the third cycle.





EXP12180 (12V 18Ah)














Relationship Between Charging Voltage And Temperature





Life Characteristics Of Standby Use



(Note) All above information shall be changed without prior notice, ExpertPower reserves the right to explain and update the latest infomation.