



Old Town

Charming shops and cafes line the winding maze of cobblestone streets in Gamla Stan, Stockholm's historic "old town" core. Visitors fall in love with the colorful buildings that give Gamla Stan its enchanting atmosphere. With a classic herringbone pattern and stain-free, matte acrylic finish that showcases the oak's natural beauty, Old Town brings a touch of old-world appeal to your home.

PRODUCT DETAILS

| | |
|---------------------|--|
| Surface Treatment | Matte finish |
| Dimensions | 2.76 x 19.29" |
| Weight per Package | 29.3 lbs |
| Area per Package | 22.6 sq. ft. |
| Package Info | Package may contain start and stop boards. |
| Installation Method | Glue Down |

CHARACTER DESCRIPTION

Even color with minor variations. Small sized knots in limited numbers allowed.

COLOR CHANGE

Some muting of color variation to medium, straw brown.

DESCRIPTIONS & IMAGERY

All samples, images and product description, plus photo and brochure specifications are there for the sole purpose of giving an approximate idea of the items described in them. They shall not form part of the contract or have any contractual force and should be viewed for illustrative purposes only. We cannot guarantee that your computer's display or the quality of the print will accurately reflect the color of the products. Your product may vary slightly from the images within this literature.

FACTS

| | |
|-------------------------|--------------------|
| Wood Species | European White Oak |
| Country of Origin | Sweden |
| Grading | Calm |
| Resandable | 2 times |
| Natural/Stained | Natural |
| Joint | Tongue & Groove |
| Floor Heating | Yes |
| Warranty | 30 Years |
| Wear Layer Material | Hardwood |
| Wear Layer Thickness | 1/8" |
| Core Material | Birch plywood |
| Core Material Thickness | 7/16" |
| Overall Thickness | 9/16" |

TECHNICAL PROPERTIES

| | |
|--|------------------------|
| Moisture Content | EN13183 7%±2% |
| Minimum Mean Density kg/m ³ | >500 kg/m ³ |
| Reaction to Fire | EN13501-1 Cfl-s1 |
| Formaldehyde Emission | EN717-1 E1 |
| Content PCP | CEN/TR14823= 5 x 10-6n |
| Breaking Strength N/mm ² | EN1533 NPD |
| Thermal Conductivity | EN12664 0.14 W/mK |
| Thermal Resistance R-Value | .08 (m2K/W) |
| Biological Durability | EN350-2 Class 1 |
| CARB2 | Compliant |
| Slipperiness | CEN/TS15676 NPD |