

Sisu

Grit, tenacity, resilience, guts - "sisu" is the Finnish art of courage. We couldn't think of a floor more fitting of that name than this soft blonde, herringbone white oak. Sisu puts the strength in your hands to create a timeless herringbone floor. Gone are the days of costly, traditional sand and finish installation processes. Our left and right planks fit together simply, resulting in an instantly smooth, table-top flat, bevel-free surface.

PRODUCT DETAILS

Surface Treatment	Matte finish
Dimensions	2.76 x 19.29"
Weight per Package	29.3 lbs
Area per Package	22.6 sq. ft.
Package Info	Package may contain start and stop boards.
Installation Method	Glue Down

CHARACTER DESCRIPTION

Even color with minor variations. Small sized knots in limited numbers allowed.

COLOR CHANGE

Stained product - noticeable color change over time.

FACTS

Wood Species	European White Oak
Country of Origin	Sweden
Grading	Calm
Resandable	2 times
Natural/Stained	Stained
Joint	Tongue & Groove
Floor Heating	Yes
Warranty	30 Years
Wear Layer Material	Hardwood
Wear Layer Thickness	1/8"
Core Material	Birch plywood
Core Material Thickness	7/16"
Overall Thickness	9/16"

TECHNICAL PROPERTIES

Moisture Content	EN13183 7%±2%
Minimun Mean Density kg/m³	>500 kg/m ³
Reaction to Fire	EN13501-1 Cfl-s1
Formaldehyde Emission	EN717-1 El
Content PCP	CEN/TR14823≤ 5 x 10-6n
Breaking Strength N/mm²	ENI533 NPD
Thermal Conductivity	EN12664 0.14 W/mK
Thermal Resistance R-Value	.08 (m2K/W)
Biological Durability	EN350-2 Class 1
CARB2	Compliant
Slipperiness	CEN/TSI5676 NPD

DESCRIPTIONS & IMAGERY

All samples, images and product description, plus photo and brochure specifications are there for the sole purpose of giving an approximate idea of the items described in them. They shall not form part of the contract or have any contractual force and should be viewed for illustrative purposes only. We cannot guarantee that your computer's display or the quality of the print will accurately reflect the color of the products. Your product may vary slightly from the images within this literature.