


C4 – STEP


by **Gabriel**




2440 - 63012




2440 - 61103




2440 - 62057



2440 - 68119




2440 - 68121




2442 - 63075



2442 - 61103



2442 - 62057




2442 - 68119




2442 - 68121




2440 - 67004



2440 - 65011



2440 - 66019



2440 - 60999



2442 - 67004



2442 - 65011



2442 - 66019



2442 - 60011



WIDHT/ ANCHO/ LARGEUR: 140cm
WEIHT/ PESO/ POID: 470gr/m2

Composition:

100% trevira CS.

Light fastness:

5 - 7, ISO 105 B02.

Abrasion:

100.000 Martindale EN ISO 12947.

Resistance to pilling:

4 - 5, ISO 12945-2.

Fastness to rubbing:

Wet 4 - 5, Dry 4 - 5, ISO 105 X12.

Flammability:

California Bulletin CAL 117-E-Class 1 • IMO MSC 307 (88) Annex 1 part 8 • MED Certificate IMO • DIN 4102 B1 • NFP 92-503/504/505 M1 • BS EN 1021 1&2 • BS 5852 Part 1 0,1 Cigarette & match • BS 5852 Crib 5 • Class Uno UNI 9175 Class 1 I EMME • ONORM B 3825-B1-3800-Q1 UK • FAR/JAR 25.853 (a) (i) (ii) • BS 7176 Medium Hazard • AM 18 - NF D 60-013 • Class Uno UNI 9175 Class 1 I EMME.

Environment:

Oeko-Tex • EU Ecolabel • 100% free of heavy metals.

Composición:

100% trevira CS.

Solidez a la luz:

5 - 7, ISO 105 B02.

Abrasión:

100.000 Martindale EN ISO 12947.

R. a la formación de pilling:

4 - 5, ISO 12945-2.

Resistencia al rozamiento:

Seco 4 - 5, Mojado 4 - 5, ISO 105 X12.

Inflamabilidad:

California Bulletin CAL 117-E-Class 1 • IMO MSC 307 (88) Annex 1 part 8 • MED Certificate IMO • DIN 4102 B1 • NFP 92-503/504/505 M1 • BS EN 1021 1&2 • BS 5852 Part 1 0,1 Cigarette & match • BS 5852 Crib 5 • Class Uno UNI 9175 Class 1 I EMME • ONORM B 3825-B1-3800-Q1 UK • FAR/JAR 25.853 (a) (i) (ii) • BS 7176 Medium Hazard • AM 18 - NF D 60-013 • Class Uno UNI 9175 Class 1 I EMME.

Medio ambiente:

Oeko-Tex • EU Ecolabel • 100% free of heavy metals.

Composition:

100% trevira CS.

Solidité à la lumière:

5 - 7, ISO 105 B02.

Abrasion:

100.000 Martindale EN ISO 12947.

Résistance au pilling:

4 - 5, ISO 12945-2.

Résistance aux frottements:

Sec 4 - 5, Humide 4 - 5, ISO 105 X12.

Inflamabilité:

California Bulletin CAL 117-E-Class 1 • IMO MSC 307 (88) Annex 1 part 8 • MED Certificate IMO • DIN 4102 B1 • NFP 92-503/504/505 M1 • BS EN 1021 1&2 • BS 5852 Part 1 0,1 Cigarette & match • BS 5852 Crib 5 • Class Uno UNI 9175 Class 1 I EMME • ONORM B 3825-B1-3800-Q1 UK • FAR/JAR 25.853 (a) (i) (ii) • BS 7176 Medium Hazard • AM 18 - NF D 60-013 • Class Uno UNI 9175 Class 1 I EMME.

Environnement:

Oeko-Tex • EU Ecolabel • 100% free of heavy metals.



16

