

Hood River Industrial LLC

PO Box 642
Mosier, OR 97040
Phone: 844-920-2280
Email: info@hoodriverind.com

Product Description Sheet

RUBBERIZEIT™ DURA-RUBBER
All Purpose Liquid Rubber Coating
www.rubberizeit.com

Product Description

Dura-Rubber is an SBR rubber base liquid rubber coating. 100% waterproof, Chemical Resistant UV Stable. Can be custom tinted in any color. Meets California low VOC standards. Easy to apply cleans up with soap and water. SBR is used in the manufacture of tires, rubber, shoes and electrical jacketing and many more rubber products.

Advantages

- Easy application
- Chemical resistant
- Tough rubber coating
- Custom tinting at no additional cost
- 100% water submersion
- Cleans up with just soap and water
- UV stable
- Low VOC
- Single part

Typical Application

- Ponds & Koi ponds
- Swimming pools
- Concrete floors
- Tool coating
- Metal roofs
- Refrigerated areas
- Traffic areas
- And more

Directions for use

1. Can be applied with a brush, roller, Sprayed or dipped.
2. Mix well to prevent uneven drying
3. Clean surface of all dirt, grease, adhesives and organic materials.
4. Application temperature 50F and rising
5. Dry time depends on temperature & Humidity. See application pages for dry times.
6. For waterproofing use reinforcement fabric at all seams, joints and inside and outside corners

Application Instructions

<https://rubberizeit.com/pages/application-instructions>

Coverage (assumes smooth surface)

- Floors, Walls, Decks 100-120 sf per gallon.
- Ponds, Pools, Cisterns any application with 100% water saturation 30-40 sf per gallon
- Roofs 50-60sf per gallon
- Contact support for any specialty applications

Technical Tips for working with Dura-Rubber

- The higher the temperature the faster the drying time 70F dry time can be as little as 30 min.
- Once dry it will be waterproof.
- Make sure surface is at least 50F for proper adhesion.
- Add rubber aggregate for non-slip or extra durability.

Thermal Properties

- Low Temperature Range -60° F to -30° F
- Minimum for Continuous Use (Static)-60° F
- Brittle Point -80° F
- High Temperature Range +210° F to +250° F
- Maximum for Continuous (Static)+225° F

Typical curing time

@60F cure time is 7 days
Do not submerge in water 24/7 until fully cured.

For safe handling information consult the Material Data Safety Sheet (MSDS)

Storage

Product shall be ideally stored in cool dry location in unopened containers at a temperature between 42F to 82F
Shelf life in unopened container is 6 months.

Environmental Performance

• Color ability	Good
• Flame Resistance	Poor
• Gas Permeability	Fair
• Odor	Good
• Ozone Resistance	Good to Excellent
• Oxidation Resistance	Good to Excellent
• Radiation Resistance	Poor to Good
• Steam Resistance	Good to Excellent
• Sunlight Resistance	Good to Excellent
• Weather Resistance	Good to Excellent
• Water Resistance	Good to Excellent

Resistance

• Oil	Good to Excellent
• Hydraulic fluid	Good to Excellent
• Gas	Good
• Diesel	Good to Excellent
• Acids diluted	Good
• Acids concentrated	Fair to Good
• Electrical properties	Good to Excellent
• Solvents	Fair to Good

Physical Characteristic

• Weight per gallon	10.43lb
• % Solids by weight	63.55
• % Solids by volume	44.06
• PH	8.8
• Viscosity	101KU
• Low VOC	-----
• Material VOC	0.26lb/gal
• Single part VOC	0.55lb/gal
• Elongation	150-200%

Note

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, Hood River Industrial LLC specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of products. Hood River Industrial specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide.

NOT FOR PRODUCT SPECIFICATIONS. THE TECHNICAL DATA CONTAINED HEREIN ARE INTENDED AS REFERENCE ONLY.
PLEASE CONTACT LOCTITE CORPORATION QUALITY DEPARTMENT FOR ASSISTANCE AND RECOMMENDATIONS ON
SPECIFICATIONS FOR THIS PRODUCT