




6000M -- 2K Clear Matt

Description:

2K matt clear for silky-matt vehicle finishes. 6000M provides a uniform matt result with a smooth and silky feel and appearance which exceed the stringent demands of the refinish industry.

Suitable Substrates:

- **Genrock** basecoat
 - **Gen20** basecoat
-



Mix 2:1 with any of the following hardeners:

- H760 extra slow
- H750 slow
- H700 standard
- H600 fast
- H500 super fast

Potlife: 3h to 5h at 20°C



15-20% **General** Thinner
16-18s / DIN 4 mm / 20°C



Compliant 1.3 – 1.5 mm (2 spray passes)
2.0-2.5 bar inlet pressure
2 = 50 – 60 micron




HVLP 1.3 – 1.5 mm (2 spray passes)
0.7 bar atomization pressure
2 = 50 – 60 micron



Wait 15 min before increasing temperature
Bake 45 min at 60°C panel temperature



6000M -- 2K Clear Matt



15-20 min
Flash-off between coats and final flash-off



Short Wave 8 min
The object should be maintained at greater than 60cm from source



Wear suitable protection

Flash Point: 23°C (73.4 °F)

Specific Gravity: 1.01 kg/cm³

Solids Content: 48% by weight pre-dilution

VOC: 580 g/l (EU limit value for this category IIB.c being max. 840g/l)

Coverage: 6-7 m²/l at 50 micron dry film thickness (theoretical)

Gloss level: 23 units ± 5 at 60° angle

SDS: See the safety data sheet