



DESCRIPTION

- a two pack recoatable isocyanate cured, acrylic polyurethane finish
- approved to APAS-1441/2, APAS-2911/1
- conforms to AS/NZS 3750.6

PRINCIPAL CHARACTERISTICS

- unlimited recoatability
- excellent resistance to atmospheric exposure
- excellent gloss retention
- tough, flexible and abrasion resistant
- resistant to splash of mineral oils, vegetable oils and aliphatic petroleum products
- resistant to splash of mild chemicals

COLOURS AND GLOSS

- High Opacity White, Black, AS2700 Colour Card - full gloss

BASIC DATA AT 25°C

- solids content approx. 49% by volume
- mix ratio 4A:1B by volume
- typical film thickness (per coat) 50 microns(dry), 100 microns(wet)
- theoretical spreading rate 9.8 m²/l for 50 microns(dry)
- touch dry after refer curing table for details
- overcoating interval refer overcoating table for details
- full cure after 7 days
- shelf life (cool and dry place) at least 12 months

RECOMMENDED SUBSTRATE CONDITIONS AND TEMPERATURE

- previous suitable coat must be dry and free from chalking and contamination and sufficiently roughened if necessary
- oil and grease should be removed from all surfaces in accordance with AS 1627.1 solvent cleaning
- substrate temperature must be at least 5°C during surface preparation, application and curing and at least 3°C above dew point
- relative humidity should not exceed 75% during application and before the dry to handle time

INSTRUCTIONS FOR USE

- mixing ratio by volume 4A:1B
- induction time - none
- pot life at 25°C 5 hours for standard hardener, (3 hours for rapid recoat hardener). Do not use after this time even if the mix is still liquid
- stir the components and mixed product well using a mechanical mixer
- this product must be thinned with the recommended thinner before application
- thinning recommendations are given as a guide and may vary depending upon substrate temperature and weather conditions
- the temperature of the mixed product must be above 15°C, otherwise extra thinner may be required to obtain application viscosity

- too much thinner will result in lower sag resistance and slower cure
- thinner should only be added after mixing the components

- freshly catalysed material should not be added to product that has been mixed for some time
- for recommendations outside those contained in this data sheet, refer to Wattyl

APPLICATION

- **AIRLESS SPRAY**
 - recommended thinner Thinner L707
 - volume of thinner 10-20%
 - nozzle orifice..... approx. 0.33 mm (0.013 inch)
 - nozzle pressure 15 MPa (2100 psi)

- **AIR SPRAY**
 - recommended thinner Thinner L707
 - volume of thinner 15-25%
 - nozzle orifice..... 1.4 - 1.8 mm
 - nozzle pressure 0.3 - 0.4 MPa (50 - 60 psi)

- **BRUSH/ROLLER**
 - recommended thinner Thinner L724
 - volume of thinner 5-10%

The maximum dry film thickness that can be achieved when brushing/rolling is 30 microns
Multiple coats may be required to achieve the recommended dry film thickness

- **CLEANING SOLVENT** Thinner L707

SAFETY PRECAUTIONS

- flammable. Avoid contact with heat and naked flame
- avoid contact with skin and eyes
- Use gloves, mask and goggles during application
- provide adequate ventilation when using in confined spaces
- this paint contains 0.049% monomeric diisocyanate when mixed. Provide adequate ventilation during use. Breathing the vapour is dangerous. Avoid breathing of fumes. Where applied by spray, use suitable air-fed respiratory equipment/hood at all times
- this product is intended for use in industrial situations by professional applicators in accordance with the advice given on this sheet. All work involving the use and application of this product should be carried out in compliance with all relevant Health, Safety & Environmental standards and regulations and must not be used without reference to the Material Safety Data Sheet (MSDS)

**ADDITIONAL DATA****Overcoating table - with Poly U400**

Substrate temperature	Poly U400 Std PT B				Poly U400 Rapid Recoat PT B			
	5°C	15°C	25°C	35°C	5°C	15°C	25°C	35°C
Minimum interval	36 hrs	24 hrs	16 hrs	6 hrs	24 hrs	12 hrs	6 hr	3 hrs
Maximum interval	unlimited				unlimited			

- surface must be dry and free from chalking and contamination

Curing table

Substrate temperature	Poly U400 Std PT B			Poly U400 Rapid Recoat PT B		
	Touch dry	Dry to handle	Full cure	Touch dry	Dry to handle	Full cure
5°C	8 hrs	36 hrs	16 days	4 hrs	16 hrs	16 days
15°C	4 hrs	24 hrs	10 days	2 hrs	10 hrs	10 days
25°C	2 hrs	16 hrs	7 days	1 hr	6 hrs	7 days
35°C	1 hr	8 hrs	5 days	30 min	3 hrs	5 days

- adequate ventilation must be continuously maintained during application and curing

Potlife (at application viscosity)

Paint temperature	Poly U400 Std PT B	Poly U400 Rapid Recoat PT B
15°C	8 hrs	5 hrs
25°C	5 hrs	3 hrs
35°C	3 hrs	2 hrs

CUSTOMER SERVICE HOTLINE 132101 (Aust)

Wattyl® is a registered trademark of Wattyl Australia Pty Ltd.

1. This information is provided with respect to the listed Wattyl products. Wattyl recommends that: (a) you review the Technical Data Sheets (TDS) and Material Safety Data Sheets (MSDS) before you use or handle the product; (b) the product be used only in accordance with the information provided by Wattyl; (c) the product be transported, stored and handled in accordance with the information on the MSDS and relevant TDS; and (d) you thoroughly test the product, using the recommended application method on a sample of intended substrate, before using the product. 2. The information in this TDS was prepared using information gathered during product development. While Wattyl endeavours to update this information and maintain the accuracy and currency of its contents, Wattyl cannot guarantee that the information provided is wholly comprehensive. 3. For all product and non-product related information, Wattyl recommends that you conduct such additional investigations as may be necessary to satisfy yourself of the accuracy, currency and comprehensiveness of the information on which you rely in using and handling the product. If you require further information please contact your nearest Wattyl Office. 4. To the full extent permitted by law, Wattyl's liability for breach of a condition or warranty implied into the contract for sale between Wattyl and you by law is limited at Wattyl's election to: (a) the replacement of the product; or (b) payment of the cost of replacing the product.
WATTYL AUSTRALIA PTY LTD (ABN 40 000 035 914)