


Diameter, weight, breaking strength and other properties are determined according to
 DS/EN ISO 2307:2019.

Tolerance of +/- 5% on weight and breaking strength.

Nom. Ø mm	Kg / 100 m	 SK75 / SK78 t	SK99 t	DM20 t
5	1.4	3.0	3.6	2.7
6	2.1	4.0	4.8	3.6
7	2.7	6.1	7.3	5.5
8	3.5	7.7	9.2	6.9
9	4.2	9.0	10.8	8.1
10	4.6	10.0	12.0	9.0
11	6.2	13.9	16.7	12.5
12	8.5	17.8	21.4	16.0
14	12.0	22.0	26.4	19.8
16	13.0	26.1	31.3	23.5
18	19.0	36.0	43.2	32.4
20	21.0	41.0	49.2	36.9
22	26.0	51.0	61.0	46.0
24	31.5	55.0	67.0	50.0
26	36.0	65.0	78.0	59.0
28	40.0	70.0	84.0	63.0
30	43.0	78.0	94.0	70.0
32	47.0	85.0	101.0	76.0
34	53.0	94.0	113.0	85.0
36	61.0	110.0	132.0	99.0
38	72.0	133.0	160.0	120.0
40	76.5	145.0	174.0	131.0
42	84.5	155.0	186.0	140.0
44	100.0	170.0	204.0	153.0
48	120.0	180.0	216.0	162.0
52	143.0	220.0	264.0	198.0
56	180.0	275.0	330.0	248.0
60	200.0	310.0	372.0	279.0
64	230.0	350.0	420.0	315.0
72	260.0	400.0	480.0	360.0
80	300.0	470.0	564.0	423.0
88	420.0	625.0	750.0	563.0
96	560.0	750.0	900.0	675.0
104	670.0	850.0	1020.0	765.0
112	780.0	950.0	1140.0	855.0
120	870.0	1050.0	1260.0	945.0
128	1000.0	1200.0	1440.0	1080.0
136	1100.0	1325.0	1590.0	1192.0
144	1250.0	1500.0	1800.0	1350.0
152	1350.0	1600.0	1920.0	1440.0
160	1470.0	1750.0	2100.0	1575.0
168	1600.0	1900.0	2280.0	1710.0
176	1700.0	2000.0	2400.0	1800.0
184	1860.0	2175.0	2610.0	1957.0
192	1980.0	2300.0	2760.0	2070.0
200	2170.0	2500.0	3000.0	2250.0

Breaking strength