

Diameter mm	Breaking strength t	Weight kg/100 m
5	3.0	1.4
6	4.0	2.1
7	6.1	2.7
8	7.7	3.5
9	9.0	4.2
10	10.0	4.6
11	13.9	6.2
12	17.8	8.5
14	22.0	12.0
16	26.1	13.0
18	36.0	19.0
20	41.0	21.0
22	51.0	26.0
24	55.0	31.5
26	65.0	36.0

Diameter mm	Breaking strength t	Weight kg/100 m
28	70.0	40.0
30	78.0	43.0
32	85.0	47.0
34	94.0	53.0
36	110.0	61.0
38	133.0	72.0
40	145.0	76.5
42	155.0	84.5
44	170.0	100.0
48	180.0	120.0
52	220.0	143.0
56	275.0	180.0
60	310.0	200.0
64	350.0	230.0
72	400.0	260.0
80	470.0	300.0