

Valutek Latex Powder-Free 12" Glove

Part Number: VTGLPFB12

MicroTek
ISO 5-6 (Class 100-1,000)



Description: Valutek latex powder-free ambidextrous 12" glove is constructed from 100% natural rubber latex with fully textured design and beaded long cuff. This glove provides high level dexterity, is strong, reliable, durable and comfortable hand protection for operators. Packaged in a cleanroom, all Valutek gloves are tested and manufactured in ISO compliant facilities under Valutek inspection and strict process control to ensure Valutek quality standards and product specifications.

Features:

- 100% natural latex material provides the highest degree of dexterity
- 12"/290mm length with beaded long cuff
- Fully textured and smooth cuff design
- Powder-free, double chlorination and DI water rinse
- Moderate acid compatibility

Application: As part of the **Valutek Microtek product family**, this product is recommended for use in a cleanroom Class 100-1,000 (ISO 5-6) critical environment. It is also commonly used in a wide variety of applications including laboratories, general industry, food processing and service, janitorial/sanitation, pharmaceutical handling, electronics assembly and light-duty maintenance and cleanup.

Caution: This product contains natural rubber latex which may cause allergic reactions in some individuals.

VTGLPFB12 Packaging



- Outer bag contains inner bag with 2 stacks of 50 gloves. Gloves packaged cuffs on bottom, vacuum sealed, flat packed and with a carton liner. 100 ea/bag, 10 bags/case, 1000 ea/case.
- Critical environment compatible. All gloves are lot traceable with retention samples held in Quality Control for 36 months from date of manufacturing.

■ Valutek West
USA-Phoenix,AZ

■ Valutek East
USA-Albany,NY

■ Valutek Asia Sdn. Bhd
Malaysia

■ Valutek P.R.C.
China

VALUTEK®

p 800.763.1250 • f 602.252.1972 • info@valutek.com

www.valutek.com

Valutek Latex Power-Free 12" Glove

Part Number: VTGLPFB12



VTGLPFB12 Physical Properties

Part Number	Size	Palm Width (mm)	Weight (gm)	Length (inch/mm)	Test Method
VTGLPFB12-SM	SM	85 ± 5	6.5 ± 0.2	12"/290mm	IEST-RP-CC005.4 ASTM D3767
VTGLPFB12-MD	MD	95 ± 5	7.0 ± 0.2		
VTGLPFB12-LG	LG	105 ± 5	7.5 ± 0.2		
VTGLPFB12-XL	XL	115 ± 5	8.0 ± 0.2		
VTGLPFB12-2X	2X	125 ± 5	8.5 ± 0.2		

Tensile Properties	Tensile Strength	Ultimate Elongation	Test Method	Measured Points	Thickness	Test Method
Before Aging	21 MPa, min	700%, min	ASTM D412	Fingertip	5.91 mil 0.15 mm	ASTM D3767
After Aging	16 MPa, min	500%, min		Palm	5.12 mil 0.13 mm	
				Cuff	3.94 mil 0.10 mm	

*Barrier Integrity: AQL 1.5

VTGLPFB12 Technical Performance

Attribute	Value	Units	Test Method
Particle Counts			
LPC: ≥0.5 μm	<2,400	particles/cm ²	IEST-RP-CC005.4, Sec 16.4
Non Volatile Residue (NVR)			
DI Water	<2.0	μg/cm ²	IEST-RP-CC005.4, Sec 17.2
IPA	<5.0	μg/cm ²	IEST-RP-CC005.4, Sec 17.2
FTIR			
Silicone Oil, Amide, DOP	Not Detectable		IEST-RP-CC005.4, Sec 17.4

Extractable Counts (Ions)					
Sodium(Na)	<0.02	μg/cm ²	Fluoride(F ⁻)	<0.001	μg/cm ²
Potassium(K)	<0.02	μg/cm ²	Bromide(Br ⁻)	<0.001	μg/cm ²
Calcium(Ca)	<0.50	μg/cm ²	Phosphate(PO ₄ ³⁻)	<0.002	μg/cm ²
Magnesium(Mg)	<0.005	μg/cm ²	Chloride(Cl ⁻)	<1.0	μg/cm ²
Ammonium(NH ₄ ⁺)	<0.005	μg/cm ²	Sulfate(SO ₄ ²⁻)	<0.20	μg/cm ²
Nitrate(NO ₃ ⁻)	<0.50	μg/cm ²	Nitrite(NO ₂ ⁻)	<0.001	μg/cm ²
Lithium(Li)	<0.005	μg/cm ²	Aluminium(Al)	<0.01	μg/cm ²
Zinc(Zn)	<0.10	μg/cm ²	Iron(Fe)	<0.005	μg/cm ²
Copper(Cu)	<0.0004	μg/cm ²			



Gloves




Wipers



Apparel



Adhesive Mats

Safety First
Maintenance

Documentation



Glove Liners



ESD