## Valutek Nitrile Cleanroom 12" Glove

Part Number: VTGNCRB12



#### Description:

Valutek's 12" ambidextrous nitrile powder-free cleanroom glove is constructed from 100% clean, synthetic nitrile polymer and contains no rubber latex. This glove has a textured fingertip and a beaded long cuff design which offeres the ultimate cleanliness and operator dexterity with very low levels of particle and extractable counts. All Valutek gloves are tested and manufactured in ISO compliant facilities under Valutek inspection and strict process control to ensure Valutek quality standards and product specifications.



#### Features:

- 100% clean and synthetic nitrile polymer (Acrylonitrile Butadiene)
- Accelerator and sulfur free
- 12"/290 mm length with beaded long cuff
- Textured fingertips
- Powder-free, double chlorination and 18 megaohm D.I. water rinse
- Low levels of particles and extractable counts
- ESD compliant, acid and solvent compatible

#### Application:

As part of the **Valutek Nanotek product family**, this cleanroom packaged glove is recommended for use in a cleanroom Class 1-10 (ISO 3-4) critical environment. It is also recommended for use in a wide variety of applications that require an extremely clean glove such as wafer fabrication, disk drives, semiconductor, biotechnology, non-asceptic pharmaceutical and optics.

#### VTGNCRB12 Packaging





- Outer bag contains inner bag with 2 stacks of 50 gloves. Gloves packaged cuffs on bottom, vacuum sealed, flat packed and with a carton liner. 100 ea/bag, 10 bags/case, 1000 ea/case.
- Critical environment compatible. All gloves are lot traceable with retention samples held in Quality Control for 36 months from date of manufacturing.



Valutek West

Valutek East

Valutek Asia Sdn. Bhd

Valutek P.R.C.

p 800.763.1250

f 602.252.1972

info@valutek.com

# Valutek Nitrile Cleanroom 12" Glove





### **VTGNCRB12** Physical Properties

Part Number	Size	Palm Width (mm)	Weight (gm)	Length (inch/mm)	Test Method	
VTGNCRB12-XS	XS	75 ± 5	5.5 ± 0.2			
VTGNCRB12-SM	SM	85 ± 5	6.0 ± 0.2		IEST-RP-CC005.4 ASTM D3767	
VTGNCRB12-MD	MD	95 ± 5	6.5 ± 0.2	12"/290		
VTGNCRB12-LG	LG	105 ± 5	7.0 ± 0.2	12 / 230		
VTGNCRB12-XL	XL	115 ± 5	7.5 ± 0.2			
VTGNCRB12-2X	2X	125 ± 5	8.0 ± 0.2			

Tensile Properties	Tensile Strength	Ultimate Elongation	Test Method	Measured Points	Thi	ckness	Test Method
Before Aging	ng 18 MPa, min	500%, min 450%, min	ASTM D412	Fingertip	4.72 mil	0.12 mm, min	ASTM D3767
0 0	,			Palm	3.94 mil	0.10 mm, min	
After Aging	16 MPa, min			Cuff	3.15 mil	0.08 mm, min	

<sup>\*</sup>Barrier Integrity: AQL 1.5

#### VTGNCRB12 Technical Performance

Attribute	Value	Units	Test Method
Particle Counts			
LPC: ≥0.5 μm	<600	particles/cm2	IEST-RP-CC005.4, Sec 16.4
Non Volatile Residue (NVR)			
DI Water	<2.0	μg/cm2	IEST-RP-CC005.4, Sec 17.2
IPA	<5.0	μg/cm2	IEST-RP-CC005.4, Sec 17.2
FTIR			
Silicone Oil, Amide, DOP	Not Detectable		IEST-RP-CC005.4, Sec 17.4

Extractable Counts (lons)							
Sodium(Na)	< 0.02	μg/cm2	Fluoride(F-)	< 0.001	μg/cm2		
Potassium(K)	< 0.02	μg/cm2	Bromide(Br <sup>-</sup> )	< 0.001	μg/cm2		
Calcium(Ca)	< 0.30	μg/cm2	Phosphate(PO <sub>4</sub> <sup>3-</sup> )	< 0.002	μg/cm2		
Magnesium(Mg)	< 0.005	μg/cm2	Chloride(Cl <sup>-</sup> )	< 0.20	μg/cm2		
Ammonium(NH <sub>4</sub> +)	<0.005	μg/cm2	Sulfate(SO <sub>4</sub> <sup>2-</sup> )	< 0.06	μg/cm2	IEST-RP-CC005.4, Sec 17	
Nitrate(NO <sub>3</sub> -)	< 0.12	μg/cm2	Nitrite(NO <sub>2</sub> -)	< 0.001	μg/cm2		
Lithium(Li)	<0.005	μg/cm2	Aluminium(Al)	< 0.01	μg/cm2		
Zinc(Zn)	< 0.07	μg/cm2	Iron(Fe)	< 0.005	μg/cm2		
Copper(Cu)	<0.0004	μg/cm2					

ESD Properties				
Electrostatic Decay	<5 seconds	Tribo Charge	<50 V	ANGU/ECD CD1E 1
Surface resistivity	< 1 X 10E11 Ω <sup>-2</sup>			ANSI/ESD SP15.1

















Glove Liners