

Valutek Nitrile Powder-free 9.5" Glove

Part Number: VTGNPFB95

MicroTek
ISO 5-6 (Class 100- 1,000)



Description: Valutek nitrile powder free ambidextrous 9.5" glove is constructed from 100% clean synthetic nitrile polymer, contains no rubber latex, fillers or silicones and has a beaded cuff and textured fingertip design. Our specially formulated, high modulus nitrile provides unmatched operator comfort and dexterity. Packaged in a cleanroom, all Valutek gloves are tested and manufactured in ISO compliant facilities under Valutek inspection and strict process control to ensure Valutek quality standards and product specifications.

- Features:**
- 100% clean and synthetic nitrile polymer (Acrylonitrile Butadiene)
 - Accelerator and sulfur free
 - Contains no fillers, silicones or plasticizers
 - 9.5"/240 mm length with beaded cuff
 - Textured fingertips
 - Powder-free, double chlorination and DI water rinse
 - ESD compliant, acid and solvent compatible

Application: As part of the **Valutek Microtek product family**, this cleanroom packaged glove is recommended for use in a cleanroom Class 100-1,000 (ISO 5-6) critical environment. It is also commonly used in a wide variety of applications including semiconductor, pharmaceutical, food handling, laboratory work, electronic, intricate parts handling and maintenance and cleanup.

VTGNPFB95 Packaging



- Outer bag contains inner bag with 2 stacks of 50 gloves. Gloves packaged cuffs on bottom, vacuum sealed, flat packed and with a carton liner. 100 ea/bag, 10 bags/case, 1000 ea/case.
- Critical environment compatible. All gloves are lot traceable with retention samples held in Quality Control for 36 months from date of manufacturing.

■ Valutek West
USA-Phoenix,AZ

■ Valutek East
USA-Albany,NY

■ Valutek Asia Sdn. Bhd
Malaysia

■ Valutek P.R.C.
China

VALUTEK®

p 800.763.1250 • f 602.252.1972 • info@valutek.com

www.valutek.com

Valutek Nitrile Powder-free 9.5" Glove

Part Number: VTGNPFB95



VTGNPFB95 Physical Properties

Part Number	Size	Palm Width (mm)	Weight (gm)	Length (inch/mm)	Test Method
VTGNPFB95-XS	XS	75 ± 5	4.5 ± 0.2	9.5"/240	IEST-RP-CC005.4 ASTM D3767
VTGNPFB95-SM	SM	85 ± 5	5.0 ± 0.2		
VTGNPFB95-MD	MD	95 ± 5	5.5 ± 0.2		
VTGNPFB95-LG	LG	105 ± 5	6.0 ± 0.2		
VTGNPFB95-XL	XL	115 ± 5	6.5 ± 0.2		

Tensile Properties	Tensile Strength	Ultimate Elongation	Test Method	Measured Points	Thickness	Test Method
Before Aging	18 MPa, min	500%, min	ASTM D412	Fingertip	4.72 mil 0.12 mm, min	ASTM D3767
After Aging	16 MPa, min	450%, min		Palm	3.94 mil 0.10 mm, min	
				Cuff	3.15 mil 0.08 mm, min	

*Barrier Integrity: AQL 1.5

VTGNPFB95 Technical Performance

Attribute	Value	Units	Test Method
Particle Counts			
LPC: ≥0.5 µm	<2,000	particles/cm ²	IEST-RP-CC005.4, Sec 16.4
Non Volatile Residue (NVR)			
DI Water	<2.0	µg/cm ²	IEST-RP-CC005.4, Sec 17.2
IPA	<5.0	µg/cm ²	IEST-RP-CC005.4, Sec 17.2
FTIR			
Silicone Oil, Amide, DOP	Not Detectable		IEST-RP-CC005.4, Sec 17.4

Extractable Counts (Ions)					
Sodium(Na)	<0.02	µg/cm ²	Fluoride(F)	<0.001	µg/cm ²
Potassium(K)	<0.02	µg/cm ²	Bromide(Br)	<0.001	µg/cm ²
Calcium(Ca)	<0.50	µg/cm ²	Phosphate(PO ₄ ³⁻)	<0.002	µg/cm ²
Magnesium(Mg)	<0.005	µg/cm ²	Chloride(Cl)	<0.60	µg/cm ²
Ammonium(NH ₄ ⁺)	<0.005	µg/cm ²	Sulfate(SO ₄ ²⁻)	<0.20	µg/cm ²
Nitrate(NO ₃ ⁻)	<0.50	µg/cm ²	Nitrite(NO ₂ ⁻)	<0.001	µg/cm ²
Lithium(Li)	<0.005	µg/cm ²	Aluminium(Al)	<0.01	µg/cm ²
Zinc(Zn)	<0.10	µg/cm ²	Iron(Fe)	<0.005	µg/cm ²
Copper(Cu)	<0.0004	µg/cm ²			

ESD Properties					
Electrostatic Decay	<5	seconds	Tribo Charge	<50	v
Surface resistivity	< 1 X 10E11	Ω ⁻²			

