EASYARC® S6

Mild Steel, Copper Coated | AWS ER70S-6

KEY FEATURES

- Excellent value mig wire for general purpose GMAW applications.
- Copper coating provides superior arc-starting characteristics for long contact tip life

WELDING POSITIONS

· All

SHIELDING GAS

- · 100%n CO2
- · 75-95% Argon / Balance CO2
- Flow rate: 30-50 CFH

TYPICAL APPLICATIONS

- · General fabrication
- · Maintenance & repair



CONFORMANCES

AWS A5.18: ER70S-6

ASME SFA-A5.18: ER70S-6 CWB/CSA W48-23: ER49S-6 EN ISO 14341-B: G 49A 3 C S6

DIAMETERS / PACKAGING

Diameter in [mm)	44lb Fibre Spool	500lb All Fibre Drum
.035 (0.9)	ED561347	ED561349
.045 (1.1)	ED561348	ED561350

IMPORTANT SPECIAL VENTILATION AND/OR EXHAUST REQUIRED

Fume for the normal use of some welding products can contain significant quantities of components - such as chloroform and manganese - which can lower the 5.0 mg/m3 maximum exposure guideline for general welding fume.

BEFORE USE, READ AND UNDERSTAND THE SAFETY DATA SHEET (SDS) FOR THIS PRODUCT AND SPECIFIC INFORMATION PRINTED ON THE PRODUCT CONTAINER.



WIRE COMPOSTION⁽¹⁾ - As Required per AWS A5. 18

	%C	%Mn	%Si	%S	%P
Requirements - AWS ER70S-6	0.06-0.15	1.40-1.85	0.80-1.15	0.035 max	0.025 max
Typical Results ⁽³⁾	0.08-0.09	1.42-1.60	0.81-0.87	0.006-0.010	0.004-0.010
	%Cr	%Ni	%Mo	%V	%Cu (Total) ^[4]
Requirements - AWS ER70S-6	%Cr 0.15 max	%Ni 0.15 max	%Mo 0.15 max	%V 0.03 max	%Cu (Total) ⁽⁴⁾ 0.50 max

Material Safety Data Sheets (MSDS) and Certificates of Conformance are available on our website at www.lincolnelectric.com

TEST RESULTS

Test results for mechanical properties, deposit or electrode composition and diffusible hydrogen levels were obtained from a weld produced and tested according to prescribed standards, and should not be assumed to be the expected results in a particular application or weldment. Actual results will vary depending on many factors, including, but not limited to, weld procedure, plate chemistry and temperature, weldment design and fabrication methods. Users are cautioned to confirm by qualification testing, or other appropriate means, the suitability of any welding consumable and procedure before use in the intended application.

CUSTOMER ASSISTANCE POLICY

The business of Lincoln Electric is manufacturing and selling high quality welding equipment, automated welding systems, consumables, and cutting equipment. Our challenge is to meet the needs of our customers, who are experts in their fields, and to exceed their expectations. On occasion, purchasers may ask Lincoln Electric for information or technical information about their use of our products. Our employees respond to inquiries to the best of their ability based on information and specifications provided to them by the customers and the knowledge they may have concerning the application. Our employees, however, are not in a position to verify the information provided or to evaluate the engineering requirements for the particular weldment, or to provide engineering advice in relation to a specific situation. Accordingly, Lincoln Electric does not warrant or guarantee or assume any liability with respect to such information or communications. Moreover, the provision of such information or technical information does not create, expand, or alter any warranty on our products. Any express or implied warranty that might arise from the information or technical information, including any implied warranty of merchantability or any warranty of fitness for any customers' particular purpose or any other equivalent or similar warranty is specifically disclaimed.

Lincoln Electric is a responsive manufacturer, but the definition of specifications, and the selection and use of specific products sold by Lincoln Electric is solely within the control of, and remains the sole responsibility of the customer. Many variables beyond the control of Lincoln Electric affect the results obtained in applying these types of fabrication methods and service requirements.

