

AC/DC+

HARDFACING

DESCRIPTION

All-position **economical hardfacing** electrode for hardfacing carbon steels, low-alloy steels, cast steels and manganese steels subjected to **abrasion**, **moderate impacts**, **and metal-to-metal friction**.

CHARACTERISTICS

- Excellent all-position weldability, even on AC power supply
- Crack-free deposit
- Smooth arc and low spatter
- Dense and porosity-free deposits
- Easy slag removal

Deposit rating scale

| | 1 | 2 | 3 | 1 | 5 | 6 | 7 | 8 | 9 | 10 |
|-------------|---|---|---|---|---|---|---|---|---|----|
| METAL-METAL | | | | | | | | | | |
| CORROSION | | | | | | | | | | , |
| IMPACT | | | | | | | | | | |
| ABRASION | | | | | | | | | | |

Hardness (as-welded): 55 - 60 HRC
Deposit thickness: 3 passes maximum

TYPICAL APPLICATIONS

Crusher jaws, plow blades, excavation equipment, pulleys, guides and transport rails, chisels, scrapers, bucket teeth, etc.

PROCEDURE

Remove any trace of oil, grease and/or dirt from the surface. Remove damaged metal with **Soudotec 212 SP** or **Soudotec G12**. Keep a short arc with the electrode slightly inclined. Remove slag between passes. If more than three passes are required, use **Soudotec 340** or **Soudotec 342** as a cushion.

MECHANICAL PROPERTIES

Diameter: 5.0 mm (3/16") 4.0 mm (5/32") 3.2 mm (1/8") 2.5 mm (3/32") Amperage: 180 - 230 A 140 - 175 A 110 - 135 A 65 - 100 A

Also available in flux-cored wire: Soudotec FC 8332W and solid MIG wire: Soudotec M600

Rev. : 7_01

Specialized welding alloys and technology. For technical assistance or for ordering:



2341, 46° avenue
Lachine (Mtl), Québec
info@fsh-welding.ca
www.fsh-welding.ca

 $\begin{array}{c} \text{T\'el} \ : \ 514.631.7670 \\ 1.800.361.9097 \\ \text{Fax} \ : \ 514.636.3339 \end{array}$