

Veneers:

Bonding & Cementation Simplified Courtesy of Dr. Bob Margeas, DDS



LAB

Sandblast (with glass, not aluminum oxide powder)

DENTIST

- · Try-in Veneers
- · Clean with alcohol and dry thoroughly
- Etch with Hydrofluoric Acid (9.0 or 9.5% HF Etch)
 - 90 seconds for feldspathic porcelain
 - · 20 seconds for e-Max
- Apply Silane (1-2 coats, air dry / min. dwell time 30 seconds)
- · Apply a thin layer of adhesive (unfilled resin, preferably hema-free) do not light
- · Apply luting cement to internal surface of veneer and proceed with seating of veneers

*this method will yield the highest bond strengths as the etching and silanization is controlled by the clinician.



LAB

- Etch with Hydrofluoric Acid (9.0 or 9.5% HF Etch)
 - 90 seconds for feldspathic porcelain
 - · 20 seconds for e-Max

DENTIST

- Apply Silane (1-2 coats, air dry / min. dwell time 30 seconds)
- · Try-in veneers
- Clean with alcohol & dry thoroughly
- · Apply a thin layer of adhesive (unfilled resin, preferably hema-free) do not light
- Apply luting cement to internal surface of veneer and proceed with seating of

*this method yields excellent results but it is recommended to check that your lab is etching for the correct amount of time to ensure the veneers are not being over-etched.





Weneers:

Bonding & Cementation Simplified Courtesy of Dr. Bob Margeas, DDS

OPTION 'C' **LESS IDEAL***

ΙΔΒ

- Etch with Hydrofluoric Acid (9.0 or 9.5% HF Etch)
 - · 90 seconds for feldspathic porcelain
 - · 20 seconds for e-Max
- Prime with Silane (1-2 coats, air dry / min. dwell time 30 seconds)

DENTIST

- Try-in veneers
- Clean with alcohol & dry thoroughly
- Apply a thin layer of adhesive (unfilled resin, preferably hema-free) do not light
- · Apply luting cement to internal surface of veneer and proceed with seating of

*this method will still lead good results but there is a higher risk of debonding if etching and silanization is not done properly by the lab.

HELPFUL TIPS

TOOTH PREPARATION

- For best results, it is recommended to use a Universal or Total-Etch adhesive system with the total-etch technique.
- · Air thin adhesive well to evaporate ethanol and ensure there is no pooling light cure.

VENEER PREPARATION & CEMENTATION

- Over-etching a veneer can lead to debonding. If you can see a white precipitate on the veneer, it has been over-etched. You can apply phosphoric acid to help remove the precipitate before applying silane.
- If you do not place many veneers, a 2-part silane is recommended for maintain freshness. Single-bottle, prehydrolized silane can become ineffective if not used in the recommended amount of time. If a silane is not "fresh", it can act as a separator and can lead to the debonding of your veneers.
- · Applying heat to the silane can improve the silanization process.
- · For best results, it is recommended to use an unfilled, hema-free, bonding resin on the internal surface of the veneer.
- · For best results, it is recommended to use a light-cured luting cement. Light-cure materials allow for more working time and are less likely to discolour over time. Choice 2 by BISCO is specifically formulated for color stability (Delta E <1.2**) resulting in high esthetics.

