



NIPPON SEIRO CO., LTD.

MANUFACTURER: PARAFFIN WAX MICROCRYSTALLINE WAX

10F, KYOBASHI SOUSEIKAN BLDG, 2-5-18 KYOBASHI CHUO-KU, TOKYO 104-0031, JAPAN

TEL: 81-3-3538-3064, FAX: 81-3-3538-3094

SPECIFICATION

FULLY REFINED PARAFFIN WAX 140/145 (60J)

| ITEM | TEST METHOD | UNIT | SPECIFICATION |
|---------------|-----------------|---------|---------------|
| MELTING POINT | ASTM D87 | °C | 60.0 – 62.8 |
| OIL CONTENT | ASTM D721 | MASS% | 0.40 MAX |
| PENETRATION | ASTM D1321 | AT 25°C | 9 – 15 |
| PENETRATION | ASTM D1321 | AT 35°C | 14 – 20 |
| COLOR | ASTM D156 | | +30 |
| REACTION | JIS K2252 | | NEUTRAL |
| UV ABSORBANCE | FDA 178.3710(B) | | PASS |

※Test method is based on JIS and is considered an equivalent test method corresponding to ASTM.