

# RESBUILD DPM

## **Description**

Resbuild DPM is a two pack Epoxy resin-based primer/coating, which has been developed to function as a residual construction moisture suppressant, allowing the early installation of moisture sensitive flooring in fast track building programmes.

One or two coats may be applied depending on the degree of dampness present in the sub-floor.

The product is available in grey, red, and clear colours to allow control of uniform coverage.

Resbuild DPM is also suitable for priming damp, minimally prepared substrates.

#### **Typical Uses**

As a surface damp-proof membrane.

As a moisture suppressant on concrete and sand/cement screeds

As a damp tolerant primer for concrete and resin screeds. As a surface tolerant coating.

## **Advantages**

- Provides surface damp-proof membrane
- Allows rapid laying of floor toppings to power floated concrete
- Solvent free, low odour
- Coloured to monitor progress
- Low viscosity, easily applied
- Excellent adhesion
- Surface tolerant
- Excellent resistance to water, grease and oil

### **Typical Properties**

Pot life @ 20°C: 45 Minutes Pot life @ 10°C: 90 Minutes

Colours: Grey, Red and Clear (BS4800 and RAL colours

can also be supplied)

Tack Free Time @20°c: 6 hours Hard Dry Time @ 20°c: 14 hours Coverage: 3 m²/kg first coat 4m²/kg second coat Adhesive strength to damp concrete:

3.6MPa (concrete failure). Flexural Strength: 64 MPa.

Water Absorption: <0.2% after 7 days immersion. Viscosity: 750 – 950 cps @ 20°c (clear grade)

### **Packaging**

Resbuild DPM is supplied in 5kg, and 15kg packs

## **Procedure**

#### **Surface Preparation**

Concrete surfaces shall be sound, clean and free from dust laitance and other contaminants. Suitable mechanical treatments such as vacuum grit blasting is recommended to ensure the removal of contaminants and to provide a 'key' for the Resbuild DPM.

Moisture testing of the substrate in accordance with BS8203, shall be carried out on new concrete floors. A sub floor moisture reading of 97% R.H. can be accommodated by Resbuild DPM.

If readings exceed this figure, then the floor must be allowed to dry out further.

#### **Mixing**

Pour the contents of the CURING AGENT tin into the BASE container and thoroughly mix, preferably by mechanical means until a uniform colour and consistency is achieved.

#### **Application**

a) Two coat application (R.H.>92%).

Apply a first coat of Resbuild DPM red, by brush or roller to the prepared substrate at a nominal rate of 3 m²/kg Within 24 hours apply a second coat at a nominal rate of 4 m²/kg

b) Single coat application (R.H<92%).

Apply a coat of Resbuild DPM (grey, red, or clear) at a nominal rate of 3 m<sup>2</sup>/kg

#### **Equipment Cleaning**

Clean equipment with Resbuild Toolclean prior to curing of the material.

#### **Storage and Shelf Life**

Store in dry conditions at temperatures between  $10^{\circ}\text{C}$  and  $25^{\circ}\text{C}$ .

Do not expose to freezing conditions.

Resbuild DPM has a minimum shelf life of 12 months when stored in original, unopened containers in accordance with manufacturer's instructions.

#### Limitations

Do not apply to surfaces with standing water. Do not apply at temperatures of 3°C or less.



# RESBUILD DPM

# **Health and Safety**

Avoid contact of the material with skin and eyes Wear gloves and goggles Wash off splashes immediately with soap and water Please refer to Material Safety Data Sheet for additional information

Resbuild DPM shall be applied strictly in accordance with the manufacturers instructions

For specific advice regarding any aspect of this product, please consult our Technical Department.

The information provided in this Product Data Sheet is intended for general guidance only and is given in good faith based on Resin Building Products Limited current knowledge and experience. No warranty in respect of fitness for a purpose, or any other liability whatsoever can be inferred from the information contained within this data sheet. Users should determine the suitability of the materials for their particular application and should always refer to the most recent issue of the Product Data Sheet for the product concerned. All materials are supplied in accordance with our standard terms and conditions of sale (available upon request).