



Epoxy TX Color AS

Pigmented, conductive textured coating

Colour	Availability	
	Quantity per pallet	
	Size / Quantity	25 kg
	Type of container	Tin bucket
	Container code	26
	Art. no.	
special colours from 100 kg	6816	■

Application rate See application examples

Range of use ■ Textured coating

Property profile

- Slip-resistant
- Conductive
- Can be subjected to mechanical loads
- Can be subjected to chemical loads
- Physiologically harmless once fully cured

Characteristic data of the product

■ On delivery			
	Component A	Component B	Mixture
Density (20 °C)	1.62 g/cm ³	1.05 g/cm ³	1.44 g/cm ³
Viscosity (25 °C)	thixotropic	130 mPa s	thixotropic
■ Once fully cured			
Reaction to fire (DIN EN 13501-1)	B _{fl} -s1* (Low Flammability)		
Slip resistance class (DIN EN 51130:2014)	R9		

* Fire test class in defined systems (see test report on fire classification: Remmers conductive systems).

The values stated represent typical characteristic data of the product and are not to be understood as binding product specifications.

Certificates > [Prüfbericht Brandklassifizierung - Remmers ableitfähige Systeme](#)

Preparation

- Substrate requirements
The substrate must be firm, dimensionally stable, capable of bearing loads and free of loose constituents, dust, oil, grease, rubber marks and other substances that could interfere with adhesion.
The adhesive pull strength of the surface after priming must be at least 1.5 N/mm² on average (smallest single value min. 1.0 N/mm²), compressive strength at least 25 N/mm².
Suitable Remmers epoxy primers, epoxy scratch coats or epoxy mortars must always be used.
- Substrate preparation
Before the application of the product a smooth surface must be produced, e.g. with a scratch coat.
Epoxy Conductive must be applied according to the current Technical Data Sheet as transverse conducting layer.
Refer to the current Technical Data Sheet for detailed information on the single products.

Production of the mixture

- Combi-container
Add the entire quantity of the hardener (component B) to the base compound (component A).
Pour the mixture into a separate container and mix again thoroughly.
Mix for at least 3 minutes.
Mix thoroughly with a slow-speed electric mixer (approx. 300 - 400 rpm).
Insufficient mixing is indicated by streaks forming.

A : B 83 : 17




Mixing ratio (A : B)

83 : 17 parts by weight

Once prepared, pour the entire mixture onto the prepared surface, spread using a suitable tool, and add texture immediately.

Directions



- **Conditions for use**
Temperature of the material, air and substrate: from min. +12 °C to max. +25 °C.
After application, protect the surface for at least 48 hours from exposure to water and moisture.
Relative humidity should not exceed 80%.
The temperature of the substrate must be at least 3 °C above the dew point temperature during application and curing.
- **Working time (+20 °C)**
Approx. 30 minutes
- **Drying time (+20 °C)**
Foot traffic after 16 hours, mechanical loads after 3 days, full loading capacity after 7 days.

As a general principle, higher temperatures will reduce and lower temperatures will increase the times stated.

Application examples

- **Textured coating**
Pour the material onto the prepared substrate and then distribute using a suitable tool, e.g. a notched trowel or notched scraper.
Work through with a suitable structured roller and work through again with another structured roller in one direction without any pressure.

Application rate

approx. 0.5 - 0.6 kg/m² binder

Notes

Unless otherwise specified, all of the values and application rates given above have been determined under laboratory conditions (20 °C) using standard colours. Slight deviations from these values may arise if the product is worked with on site.

When coating continuous surfaces, only use materials with the same batch number as slight differences in colour, gloss and texture may occur.
Take the black colour of the transverse conducting layer into consideration when selecting the colour of the subsequent coating.
Before the application of the covering layer, the correct functioning of the transverse conducting layer and of the connections must be proved and registered in a measurement report.
Low levels of air humidity can cause a higher discharge resistance, uneven or thicker layers can even lead the coating to not be conductive at all.
The resulting surface texture is strongly influenced by the conditions on site and the application method. Therefore, surface texture is not covered by product liability.
Low thickness and low temperature can affect the visual effect of the finished surface.
Depending on the application and system, pores may be created due to air pockets when texturing the thixotropic coating material. These may accumulate dirt during use.
Abrasive mechanical loads leave traces of wear.
Suitable for vehicle traffic with rubber tyres; not suitable for vehicle loads with metal or polyamide tyres nor for dynamic point loads.
Low levels of air humidity can cause a higher discharge resistance, uneven or thicker layers can even lead the coating to not be conductive at all.
Epoxy resins are generally not colourfast when exposed to UV light or weather.
In case of repairs on the surface or working up to existing surfaces, there will be a visible transition in appearance and texture.
Anti-slip floors naturally require more cleaning effort than smooth surfaces. Therefore, the use of cleaning machines with soft brushes is recommended.
Further notes on working, system construction and maintenance of the listed products can be found in the latest Technical Data Sheets and the Remmers system recommendations.


Tools / Cleaning



Notched trowel, notched scraper, suitable textured roller, suitable mixer

More detailed information can be found in the Remmers Tool Programme.
Clean tools, equipment and splashed material immediately while fresh with V 101 Thinner.
Take suitable protective and waste disposal measures when cleaning.

Storage / Shelf life



If stored unopened in the original container and kept cool, dry and protected from frost, min. 12 months (component A)/min. 24 months (component B).

Safety data / Regulations

For professional users only!



For further information on the safety aspects of transporting, storing and handling the product and on disposal and environmental matters, please see the current Safety Data Sheet and the brochure entitled "Epoxy Resins in the Construction Industry and the Environment", issued by Deutsche Bauchemie e.V. (2nd edition 2009).

Disposal

Larger quantities of leftover product should be disposed of in the original containers in accordance with the applicable regulations. Completely empty, clean containers should be recycled. Do not dispose of together with household waste. Do not allow to enter the sewage system. Do not empty into drains.

VOC content as per the
"Decopaint" Directive
(2004/42/EC)

EU limit value for the product (cat A/j): max. 500 g/l (2010).
This product contains < 500 g/l VOC.

VOC	
Kat. 2010:	A/j
max.: 500g/l	

Declaration of conformity



Remmers GmbH
Bernhard-Remmers-Str. 13, D – 49624 Lönningen

20
GBIII 153
EN 13813:2002
6816

Synthetic resin screed for use internally in buildings

Reaction to fire:	E _n
Release of corrosive substances:	SR
Wear resistance:	≥ AR 1
Bond strength:	≥ B 1.5
Impact resistance:	≥ IR 4

Please note that the data and information given above have been calculated as guidelines in the laboratory and from real-life experience and are therefore not binding as a basic principle.

This information is therefore of a general nature only and describes our products and how they are used and worked with. In this respect, it must be borne in mind that the varied and diverse nature of the

prevailing working conditions, materials used and construction sites encountered means that not every individual case can be covered. In this respect, we therefore recommend either conducting tests or liaising with us in the event of any doubt. Unless we have provided express written assurance of the products' specific suitability or characteristics in respect of a contractually stipulated intended use, any technical application-related advice or instruction will never

be binding, even though it is provided to the best of our knowledge. In all other respects, our general terms and conditions of sale and delivery shall apply.

When a new version of this Technical Data Sheet is published, it shall replace the previous version.