



# Clean Galena

Cleaner for emission-free cleaning of mineral surfaces

Type/Name	Availability		
	Quantity per pallet	288	18
	<b>Packaging unit</b>	<b>1 kg</b>	<b>25 kg</b>
	Type of container	Plastic bucket	Plastic bucket
	Container code	01	25
	<b>Art. no.</b>		
Clean Galena	0661	■	■
<b>Special formulation</b>			
Clean Galena individual	0664		■
Upon consultation only, lead time min. 2 weeks, minimum order quantity approx. 4,000 kg			

## Application rate

Approx. 2 - 3 kg/m<sup>2</sup> on even surfaces

Determine the precise application rate on a sufficiently large, representative trial surface. When mixing with Clean Galena neutral, the application rate is reduced according to the mixing ratio.



## Range of use



- Mineral surfaces, in particular limestone
- Reduction of heavy metals, in particular lead
- Reduction of encrusted dirt
- Removal of stains caused by iron or copper compounds
- For use by professionals

## Property profile



- Gentle cleaning
- Emission-free
- Dries to form an easily removable skin that binds surface impurities
- Binds impurities in the surface
- Complexes heavy metals

## Characteristic data of the product

Density (20 °C)	1.18 g/ml
pH value	Approx. 10.0

The values stated represent typical characteristic data of the product and are not to be understood as binding product specifications.

## Possible system products

- [Clean Galena neutral \(0662\)](#)

## Preparation

- **Substrate requirements**



Stable and free of dust.

The substrate must be free from biological contamination such as moss, algae and mould.

**■ Substrate preparation**

Use a suitable tool to coarsely clean off the substrate.

Set up a trial area to determine the cleaning effect.

Take appropriate measures to protect adjacent building elements and materials that should not come into contact with the product.

Thoroughly pre-wet the substrate.

**Directions**

For professional users only!



**■ Conditions for use**

Temperature of the material, air and substrate: from min. +5 °C to max. +30 °C

Stir well.

If necessary, mix the material with Clean Galena neutral in order to adjust the cleaning effect and drying behaviour. Document the mixing ratio.

Apply to the entire surface area of the substrate using a suitable tool.

Fill undercut areas and contours thoroughly with the material.

Once completely dry (usually 24 hours after application), remove the film by carefully detaching using a spatula.

After removing the skin, clean the treated surface with fresh water starting from the highest point.

Further cleaning procedures might be necessary, depending on the degree of contamination and the substrate.

If needed, repeat the application.

**Tips on use**

Please contact Remmers Technical Service (phone +49 5432 83-153) before applying with machine processing.

The drying time depends on the substrate, the coating thicknesses and the climate conditions.

**Notes**

Always set up a sufficiently large, representative trial area or areas!

Deviations from applicable regulations must be agreed separately.

The relevant test certificates must be observed when planning and carrying out work.

**Tools / Cleaning**


Brush, scraper, smoothing trowel, airless spraying equipment, peristaltic pumps



Clean tools immediately after use with water and detergent.

**Storage / Shelf life**

If stored unopened in its original container in a cool, dry place and protected against frost, the product will keep for at least 12 months.



**Safety data / Regulations**

For further information on the safety aspects of transporting, storing and handling the product and on disposal and environmental matters, please see the current Safety Data Sheet.

**Disposal**



Larger quantities of leftover product should be disposed of in the original containers in accordance with the applicable regulations. Completely empty, clean containers should be recycled. Do not dispose of together with household waste. Do not allow to enter the sewage system. Do not empty into drains.

Any material that is contaminated after application must be disposed of in accordance with the applicable regulations.

Detergents Regulation  
(EC) No 648/2004

2,2-Dibromo-3-nitrilopropionamide  
1,2-Benzisothiazolinone

Please note that the data and information given above have been calculated as guidelines in the laboratory and from real-life experience and are therefore not binding as a basic principle.

This information is therefore of a general nature only and describes our products and how they are used and worked with. In this respect, it must be borne in mind that the varied and diverse nature of the

prevailing working conditions, materials used and construction sites encountered means that not every individual case can be covered. In this respect, we therefore recommend either conducting tests or liaising with us in the event of any doubt. Unless we have provided express written assurance of the products' specific suitability or characteristics in respect of a contractually stipulated intended use, any technical application-related advice or instruction will never

be binding, even though it is provided to the best of our knowledge. In all other respects, our general terms and conditions of sale and delivery shall apply.

When a new version of this Technical Data Sheet is published, it shall replace the previous version.