

# Reactive stain



5L 1L

As with all wood finishing always do a test area first to safeguard against an undesirable outcome. This technical data sheet is merely a guide and not a guarantee. All products are formulated to the best of our knowledge. The information is given as a result of many years experience. This product has had extensive tests carried out.

**Ciranova North-America**  
1255 22nd Street  
San Francisco, CA 94107  
tel. 415. 282. 2529 fax 415. 477. 2106  
info@ciranova-na.com

[www.ciranova-na.com](http://www.ciranova-na.com)

## PRODUCT DESCRIPTION

Ageing stain based on natural and chemical dyes.

## TECHNICAL DATA

COLOURS	available in 16 colours
LUSTRE	-
DENSITY	+/- 1,00 kg/l
VISCOSITY	like water

## USE

Reactive stains are particularly suitable for wood containing tannin such as oak and pine. For interior use only.

## PREPARATION

Sand the wood. Remove carefully sanding dust.

## USER TIPS

Before using, stir and shake well. Apply the reactive stain with a brush in the direction of the fiber and evenly distribute with a dry brush. Attention: It's a reactive stain, apply the stain equally!



## DRYING TIMES

6 hours at room temperature. (reaction time)



## APPLYING QUANTITY

75-129 sq ft/l. Depending on type of wood and sanding.

## AFTER TREATMENT

Sand with fine sanding paper after drying. Can be treated afterwards with wax or oil. For Vanish, please contact our technical service.

## PRODUCT INFORMATION

16 colours available.

Shelf life: 1 year in original en wel closed packaging

Must be stored in a frost free place.

## SPECIAL QUALITIES

Only use stainless material. After use, clean the material with water. This product should not be poured into drains.

**Stains should always be tested before the surface treatment. Used sanding grain, type of wood, ..... may affect the final colour.**