

TEST REPORT

CLIENT PID Floors

TEST METHOD CONDUCTED

ASTM D7027 (Hoffman) Evaluation of Scratch Resistance using a

Scratch Machine



DESCRIPTION OF TEST SAMPLE		
IDENTIFICATION	ES Collection	
REFERENCE	Alabaster	

GENERAL PRINCIPLE

A scratch is applied onto the specimen surface under a constant normal load over a distance of 0.1 m (60.0001 m) at a constant scratch rate of 0.1m/s (60.0005 m/s). This test mode is intended to evaluate the load-dependent response of the material and establish the weight load required to produce scratch penetration. The constant load value was increased if the load used is insufficient to generate damage on the specimen.

TEST RESULTS

TEST RESULTS FOR HOFFMAN SCRATCH #1	7.5 N
TEST RESULTS FOR HOFFMAN SCRATCH #2	7.0 N
TEST RESULTS FOR HOFFMAN SCRATCH #3	7.5 N

APPROVED BY:

Lang asleny

This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical of similar products. This report, or the name of Professional Testing Laboratory Inc. shall not be used under any circumstance in advertising to the general public.

714 Glernwood Place Dalton, GA 30721 Phone: 706-226-3283 Fax: 706-226-6787 email: protest@optilink.us