



TEST REPORT

DATE: 03-13-2019

Page 1 of 1

TEST NUMBER: 0254548

CLIENT	PID Floors
---------------	------------

TEST METHOD CONDUCTED	ASTM D4060 Standard Test Method for Abrasion Resistance of Organic Coatings by the Taber Abraser
------------------------------	--



DESCRIPTION OF TEST SAMPLE	
IDENTIFICATION	TM Lacquer Collection
REFERENCE	TMW51

GENERAL PRINCIPLE

A test specimen is subjected to the rubbing action of two abrading wheels under controlled conditions of pressure and abrasive action. The abrasion wheels rest on the surface of the specimen which is mounted on a rotating platform. Turning of the platform initiates the abrasive action on the test specimen.

TEST RESULTS

ABRASION WHEEL	H-18
LOAD APPLIED	1,000 Grams
NUMBER OF CYCLES	100

***NOTE:** Test sample was abraded until wear layer was penetrated, this was considered the end point.

APPROVED BY:

This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical or similar products. This report, or the name of Professional Testing Laboratory Inc. shall not be used under any circumstance in advertising to the general public.