



Issued By: Document Manager
Issue Date: July 2012

DATE: 02-10-2020

TEST NUMBER:0263998

CLIENT PID Floors

TEST METHOD CONDUCTED ASTM D1308 Effect of Household Chemicals on Prganic Finishes (Modified)



DESCRIPTION OF TEST SAMPLE	
IDENTIFICATION	Foundation Line
CONSTRUCTION	Engineered Wood
REFERENCE	Grace

GENERAL PRINCIPLE

The four listed agents were applied to the wood finish and allowed to dwell for 4 hours. Bona Hard Surface Cleaner was used as a first step of removal. If the stain persists, acetone was used to clean the area. The area was rated for any remaining discoloration from the stain application using the AATCC Grey Scale for staining.

TEST RESULTS

STAINING AGENTS	RATING
Mustard	5
Shoe Polish	2.5
Black Sharpie	4
Used Motor Oil	4.5

AATCC RATING KEY	
5	No stain
4	Slight stain
3	Noticeable stain
2	Considerable stain
1	Severe stain

APPROVED BY: *Gary Colburn*

This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical of similar products. This report, or the name of Professional Testing Laboratory Inc. shall not be used under any circumstance in advertising to the general public.

714 Glenwood Place Dalton, GA 30721 Phone: 706-226-3283 Fax: 706-226-6787 email: protest@optilink.us

DATE

COMPLETED

TEST PERFORMED BY

D
R
E
/
/
R
E
B