

MYLANDS

FRICITION POLISH FOR ALL TYPES OF TURNED WOOD

| PRODUCT NAME | CODE | VOC LEVEL |
|----------------------------|-------------|-----------|
| High Build Friction Polish | 01 770 8093 | 610g/l |

PRODUCT DETAILS

A high gloss finish which brings out the beauty of wood on turned items - normally used on a lathe.

Friction Polish is a Shellac based polish carried in Methylated Spirits specially formulated for use on turned items on a lathe to give a high gloss finish.

It contains a high Shellac content which gives good build, so does not normally require a sealer coat prior to application.

It is very fast drying when used on a lathe as the friction developed in the turning process aids dry.

APPLICATION

- ◆ Friction Polish may be used over most of Mylands stain ranges.
- ◆ Always ensure the stain is dry before coating with the Friction Polish.
- ◆ Stir the Friction Polish well before use.
- ◆ Always test Friction Polish on an off-cut of timber or an inconspicuous area to check colour and finish is as desired before polishing the whole article.
- ◆ The surface of the wood must be clean, smooth, dry and free from dust, wax or other contaminants.
- ◆ If possible, work at a minimum temperature of 15°C.
- ◆ Using a lint-free cotton pad moistened with the Friction Polish, apply a thin coat to the turned wood on the lathe rotating at low speed.
- ◆ Leave for 5 – 10 minutes and then increase speed to medium and buff with a clean lint-free cotton cloth or 0000 grade wire wool.
- ◆ Take care not to use excessive speed as the polish is liable to scorching due to the high degree of friction produced.
- ◆ If required, a second coat may be applied in similar manner after 10 – 20 minutes.
- ◆ If a higher sheen is required, the finished article may be burnished using Burnishing Cream or a wax polish.

DRYING TIME



Touch dry
immediately.



Hard dry in
10-20 minutes (at 20°C).

COVERAGE

On average per litre **10-12 m²** dependant on type and absorbancy of the substrate and amount applied.

THINNERS

Friction Polish should not normally require thinning but, if desired, may be thinned with Methylated Spirits (09 802 0741).

CLEANING

Use Methylated Spirits, code (09 802 0741).

STORAGE

Store in cool conditions and replace lid on container when not in use. Shelf life can be many years if stored correctly.

MAINTENANCE


Clean polished surfaces with a damp cloth.

For more soiled surfaces a small amount of liquid detergent may be added to the water.

HEALTH AND SAFETY

Refer to Mylands Friction Polish MSDS before use.

SIZES AVAILABLE



For further information
visit our website: www.mylands.co.uk
or contact us: +44 (0)208 670 9161
sales@mylands.co.uk



By Appointment to Her Majesty Queen Elizabeth II
Manufacturers of French Polishes, Stains and Wax Polishes
John Myland Limited, London

Last updated 01.11.2020