

MYLANDS

LIGHT FAST STAINS FOR QUICK DRYING WOOD STAINING

PRODUCT NAME/COLOUR	CODE	PRODUCT NAME/COLOUR	CODE
Antique Mahogany	11 766 8021	Light Mahogany	11 766 8501
Antique Pine	11 766 8129	Mid Oak	11 766 8522
Antique Yew	11 766 8133	Old Walnut	11 766 8503
Brown Mahogany	11 766 8505	Red Mahogany	11 766 8542
Brown Oak	11 766 8518	Repro Mahogany	11 766 8504
Dark Oak	11 766 8523	Repro Yew	11 766 8600
Dark Jacobean	11 766 8506	Rosewood	11 766 8539
English Brown Oak	11 766 8551	Teak	11 766 8540
English Light Oak	11 766 8599	Walnut	11 766 8550
English Walnut	11 766 8591	Yew	11 766 8507
Golden Oak	11 766 8531	Blue	11 766 8573
Red	11 766 8574	Green	11 766 8572
Yellow	11 766 8558	White	11 766 8511
Orange	11 766 8575	Black	11 766 8520

PRODUCT DETAILS

A range of quick drying stains based on dyes dissolved in alcohol solvents.

Mylands Light Fast Stains have been formulated on selected spirit solvents and light-fast dyes to provide stains which are both light-fast and non-grain raising. The stains may be intermixed to give the precise shade required.

They may be used under all Mylands lacquer types.

The stains may be used up to a level of 20% to tint nitrocellulose, pre-catalysed and acid catalysed lacquers, but not polyurethane or waterborne lacquers.

APPLICATION

- ◆ Timber should be evenly sanded with a minimum of 180 grit paper prior to staining to ensure the stain applies and dries without patchiness.
- ◆ Light Fast Stains may also be used on flooring, but due to fast drying time, need to be used quickly - ensuring a wet edge is maintained to avoid patchiness.
- ◆ It is important that clean, white, lint-free cloth is used for application and wiping as colour could be leached out of coloured cloth by the solvents in the stain and affect the final colour.

APPLICATION METHODS

Hand ragging application:

- ◆ Use a clean, soft, white lint-free cloth and apply evenly to wet the whole surface being stained before wiping off the surplus stain with a clean lint-free cloth.

Spray/wipe application:

- ◆ Spray an even wet coat to the entire surface and wipe off the surplus with a clean lint-free cloth.

Spray/leave application :

- ◆ These stains may be dry sprayed, but care needs to be taken to ensure an even coating weight across the surface to avoid patchiness - spray to follow the grain pattern of the timber. It may help to thin the stain to assist controlling the application.

Dip application:

- ◆ Dip item into the stain, then remove and allow draining for approximately 1 minute. Finally wipe off surplus stain with a clean lint-free cloth.

MYLANDS

LIGHT FAST STAINS (CONTINUED) FOR MOST WOOD STAINING USES

COLOUR MATCHING

As mentioned above, these stains may be mixed to give other colours. However if you cannot achieve the desired colour by this method, Mylands will (for a charge) match your colour for you. You will need to supply a colour pattern and some of the substrate on which the stain will be used.

HEALTH & SAFETY

Refer to Mylands Light Fast Stain MSDS before use.

VOC LEVEL

840g/litre.

COVERAGE

On average per litre **10 m²** dependant on substrate porosity and method of application.

DRYING TIME



Less than 10-15 minutes
at 20°C before overcoating.

THINNING

If it is thought necessary to weaken these stains, use Light Fast Thinners, product code 11 766 0005, OR Methylated Spirit.

SIZES AVAILABLE

