

MYLANDS

NITROSTAINS FOR EASE OF APPLICATION

PRODUCT NAME/COLOUR	CODE	VOC LEVEL
Antique Pine	11 768 0098	86og/l
Black	11 768 0020	86og/l
Brown Mahogany	11 768 0005	86og/l
Golden Oak	11 768 0031	86og/l
Jacobean Oak	11 768 0006	86og/l
Light Oak	11 768 0021	86og/l
Old Pine	11 768 7903	86og/l
Plum Red	11 768 0041	86og/l
Red Mahogany	11 768 0042	86og/l
Repro Mahogany	11 768 0004	86og/l
Rosewood	11 768 0039	86og/l
Teak	11 768 0040	86og/l
Walnut	11 768 0050	86og/l
Yew	11 768 0007	86og/l

PRODUCT DETAILS

Mylands Nitrostains have been formulated on a selected solvent blend to provide excellent application properties.

Nitrostains are non grain raising.

Due to formulation constraints, the light-fastness of light colours is poor. Light-fastness of medium to dark shades is satisfactory – apart from black which should only be used under tinted or pigmented lacquers.

The range of stains may be intermixed to give the precise shade required. Nitrostains may only be used under Shellac Polishes and Cellulose Lacquers. They may not be overcoated with Precatalysed, Acid Catalysed or Polyurethane Lacquers.

APPLICATION

- ◆ Timber should be evenly sanded with a minimum of 180 grit paper prior to staining to ensure the stain applies and dries without patchiness.
- ◆ It is important that clean, white lint-free cloth is used for application and wiping as fibres could catch in the grain and colour could be leached out of coloured cloth by the solvents in the stain.
- ◆ It is important that any surplus stain is wiped off cleanly from the surface, as any residual stain could impair adhesion of subsequent lacquer coatings. Nitrostains may not be used to tint lacquers of any type.

APPLICATION METHODS

Hand ragging application:

- ◆ Use a clean, soft, white lint-free cloth and apply stain evenly to wet the whole surface to be stained before wiping off the surplus stain cleanly with a clean lint-free cloth.

Spray/wipe application:

- ◆ Spray an even wet coat of stain to the entire surface to be stained and wipe off the surplus stain cleanly with a clean lint-free cloth.

Dip application:

- ◆ Dip item into the stain, then remove and allow to drain for approximately 1 minute. Then wipe off surplus stain cleanly with a clean lint-free cloth.

Brush application:

- ◆ Brush an even wet coat of stain to the entire surface to be stained before wiping off the surplus cleanly with a clean lint-free cloth.

MYLANDS

NITROSTAINS (CONTINUED) FOR EASE OF APPLICATION

CLEANING

Use Standard Thinners (code 45 802 5437).

THINNING

If it is thought necessary to weaken these stains, used Nitro stain Thinners (code 86 064 1659).

HEALTH & SAFETY

Refer to Mylands Light Fast Stain MSDS before use.

COVERAGE

On average per litre **10 m²** dependant on substrate porosity and method of application.

DRYING TIME



Allow **1 hour minimum** at 20°C before overcoating.

SIZES AVAILABLE

250ml



500ml




1
litre



5
litre

Some shades
are available in



25
litre

