

Test Report

No. CANEC2300425401

Date: 16 Jan 2023

Page 1 of 5

Client Name : CERAMCOR LLC

Client Address : 12619 OLD IRON LANE CHARLOTTE, NC 28215,USA

Sample Name : Ceramic sauce pot

Country of Origin : China

The above sample(s) and information were provided by the client.

SGS Job No. : CP23-000654 - SZ

Date of Sample Received : 09 Jan 2023

Testing Period : 09 Jan 2023 - 16 Jan 2023

Test Requested : Selected test(s) as requested by the client.

Test Method(s) : Please refer to next page(s).

Test Result(s) : Please refer to next page(s).

Result Summary :

| Test Requested | Conclusion |
|---|------------|
| Regulation (EC) No 1935/2004 of the European Parliament and of the Council of 27 October 2004, German Food, Articles of Daily Use and Feed Code of September 1, 2005 (LFGB), Section 30 & 31 with amendments—Sensorial examination odour and taste test | PASS |
| Regulation (EC) No 1935/2004 of the European Parliament and of the Council of 27 October 2004, German Food, Articles of Daily Use and Feed Code of September 1, 2005 (LFGB), Section 30 with amendments & DIN51032-2017 —Leachable Lead and Cadmium | PASS |
| ALS Opinion Number 2017/15 —Leachable Cobalt | PASS |

Signed for and on behalf of
SGS-CSTC Standards Technical Services Co., Ltd. Guangzhou Branch

Ivy Ren

Ivy Ren
Approved Signatory

scan to see the report



FCC3C590



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <https://www.sgs.com/en/Terms-and-Conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.
Attention: To check the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

SGS-CSTC Standards Technical Services Co., Ltd.
Guangzhou Branch

No.198, Kezhu Road, Science City, Economic & Technological Development Area, Guangzhou, Guangdong, China 510663
中国·广东·广州高新技术产业开发区科学城科珠路198号 邮编: 510663

t (86-20) 82155555 www.sgs.com
t (86-20) 82155555 sgs.china@sgs.com

Test Report

No. CANEC2300425401

Date: 16 Jan 2023

Page 2 of 5

Test Result(s) :

Test Part Description :

| Specimen No. | SGS Sample ID | Description | Material (claimed by the client) |
|--------------|------------------|-------------|-------------------------------------|
| SN1 | CAN23-004254.001 | Ceramic lid | Ceramic |
| SN2 | CAN23-004254.002 | Ceramic pot | Ceramic |

Regulation (EC) No 1935/2004 of the European Parliament and of the Council of 27 October 2004, German Food, Articles of Daily Use and Feed Code of September 1, 2005 (LFGB), Section 30 & 31 with amendments—Sensorial examination odour and taste test

Test Method : With reference to DIN10955:2004,direct contact method.
No.of panelist:6

| <u>Test Item(s)</u> | <u>Limit</u> | <u>001</u> | <u>002</u> |
|---|--------------|-----------------|-----------------|
| Test media | - | Distilled water | Distilled water |
| Test Temperature (°C) | - | 100 | 100 |
| Test time (hr) | - | 2 | 2 |
| Sensorial examination odour (Point scale) | 2.5 | 0.0 | 0.0 |
| Sensorial examination taste (Point scale) | 2.5 | 0.0 | 0.0 |
| Comment | | PASS | PASS |

Notes :

- Intensity scale (rounded at 0.5):
- 0 – no perceptible difference
 - 1 – just perceptible difference
 - 2 – slight difference
 - 3 – marked difference
 - 4 – strong difference

Regulation (EC) No 1935/2004 of the European Parliament and of the Council of 27 October 2004, German Food, Articles of Daily Use and Feed Code of September 1, 2005 (LFGB), Section 30 with amendments & DIN51032-2017—Leachable Lead and Cadmium

Test Method : With reference to EN 1388-1: 1995 & EN 1388-2:1995. Analysis was performed by ICP-OES.

Sample 001 Hollowware



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <https://www.sgs.com/en/Terms-and-Conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.
Attention: To check the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

| | <u>Vol. of 4%HAc used (mL)</u> | <u>Depth (mm)</u> |
|-------|------------------------------------|---------------------------------------|
| 1 | 370 | 28 |
| | <u>Leachable Lead (mg/L)</u> | <u>Leachable Cad- mium (mg/L)</u> |
| 1 | <0.1 | <0.01 |
| Limit | 1.5 | 0.1 |

Sample 002 Hollowware

| | <u>Vol. of 4%HAc used (mL)</u> | <u>Depth (mm)</u> |
|-------|------------------------------------|---------------------------------------|
| 1 | 1500 | 87 |
| | <u>Leachable Lead (mg/L)</u> | <u>Leachable Cad- mium (mg/L)</u> |
| 1 | <0.1 | <0.01 |
| Limit | 1.5 | 0.1 |

Sample 001 Drinking rim

| | <u>Vol. of 4%HAc used (mL)</u> | <u>Depth (mm)</u> |
|-------|--|---|
| 1 | 230 | 28 |
| | <u>Leachable Lead (mg/article)</u> | <u>Leachable Cad- mium (mg/article)</u> |
| 1 | <0.1 | <0.01 |
| Limit | 2.0 | 0.2 |

Sample 002 Drinking rim

| | <u>Vol. of 4%HAc used (mL)</u> | <u>Depth (mm)</u> |
|---|------------------------------------|-----------------------|
| 1 | 230 | 87 |



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <https://www.sgs.com/en/Terms-and-Conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.
Attention: To check the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

| | <u>Leachable Lead</u> (mg/article) | <u>Leachable Cad-</u> <u>mium (mg/article)</u> |
|-------|---------------------------------------|---|
| 1 | <0.1 | <0.01 |
| Limit | 2.0 | 0.2 |

Notes :

Flatware: With an internal depth not exceeding 25mm, measured from the lowest point to the horizontal plane passing through the overflow point.

Hollowware: Those articles which do not fall into the category of Flatware.

Drinking rim: The drinking rim is a 20mm wide section of the external surface of a drinking vessel. The width is measured downwards from the upper edge along the wall of the vessel.

ALS Opinion Number 2017/15—Leachable Cobalt

Test Method : With reference to EN 1388-1: 1995 . Analysis was performed by ICP-OES.

Sample 001 Hollowware

| | <u>Vol. of 4%HAc</u> <u>used (mL)</u> | <u>Depth</u> <u>(mm)</u> |
|---|--|-----------------------------|
| 1 | 370 | 28 |

| | <u>Leachable Cobalt</u> (mg/L) |
|-------|-----------------------------------|
| 1 | <0.05 |
| Limit | 0.1 |

Sample 002 Hollowware

| | <u>Vol. of 4%HAc</u> <u>used (mL)</u> | <u>Depth</u> <u>(mm)</u> |
|---|--|-----------------------------|
| 1 | 1500 | 87 |

| | <u>Leachable Cobalt</u> (mg/L) |
|-------|-----------------------------------|
| 1 | <0.05 |
| Limit | 0.1 |

Unless otherwise stated, the decision rule for conformity reporting is based on Binary Statement for Simple Acceptance Rule ($w=0$) stated in ILAC-G8:09/2019.



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <https://www.sgs.com/en/Terms-and-Conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.
Attention: To check the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

Sample photo:



SGS authenticate the photo on original report only

*** End of Report ***



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <https://www.sgs.com/en/Terms-and-Conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.
Attention: To check the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com